

AD A 039488


(12)

AD

FA-TR-76073

Study of Improved Aluminum Materials for
Vehicular Armor

April 7, 1977



Final Report on Contract Number DAAA25-73-C-0657
Approved for Public Release; Distribution Unlimited



J. E. Vrugink
Aluminum Company of America
Alcoa Technical Center
Alcoa Center, PA 15069

U.S. ARMY ARMAMENT COMMAND
FRANKFORD ARSENAL
PHILADELPHIA, PENNSYLVANIA 19137

AD No. _____
DDC FILE COPY

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed. Do not return it to the originator.

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)


REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER FFA Report No. FA-TR-76073	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Study of Improved Aluminum Materials for Vehicular Armor		5. TYPE OF REPORT & PERIOD COVERED Final Report June 1973 - June 1975
7. AUTHOR(s) J. E. Vrugink		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Aluminum Company of America Alcoa Technical Center Alcoa Center, PA 15069		8. CONTRACT OR GRANT NUMBER(s) DAAA25-73-C-0657 New
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Tank Automotive Research and Development Command ATTN: DRDTA-RKA, Warren, MI 48090		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS DA Project 1X663620DG20
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) Frankford Arsenal ATTN: SARFA-PDM-P Philadelphia, PA 19137		12. REPORT DATE 7 Apr 1977
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release; Distribution Unlimited.		13. NUMBER OF PAGES 183
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		15. SECURITY CLASS (of this report) U
18. SUPPLEMENTARY NOTES		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) aluminum alloys fracture toughness plate microstructure intermediate thermal mechanical treatment final thermal mechanical treatment tensile properties		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) An Intermediate Thermal Mechanical Treatment (ITMT), consisting of warm rolling at 500°F followed by a recrystallization treatment, produced a fine-grained, relatively equiaxed, recrystallized structure in 7475 plate. Alloy 7475-T6 plate having this recrystallized structure (AR) had slightly lower strengths and fracture toughness and higher ductility (tensile reduction in area) than laboratory or commercial hot rolled 7475-T6 plate having an unrecrystallized structure. Alloy 7475-T6, similarly processed to a fine-grained, recrystallized structure, —→ over		

DD FORM 1473 EDITION OF 1 NOV 65 IS OBSOLETE


UNCLASSIFIED

1 SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

409 EUC.

- 
20. then hot rolled 25% at 750°F (AR+HR) had (1) strengths similar to laboratory and commercial hot rolled 7475-T6 plate, (2) fracture toughness similar to commercial hot rolled 7475-T6 plate but slightly lower than laboratory hot rolled 7475-T6 plate, and (3) ductility higher than laboratory or commercial hot rolled 7475-T6 plate. The fracture toughness of both the recrystallized (AR) and the recrystallized plus hot rolled (AR+HR) 7475-T6 plate was significantly higher than the fracture toughness of conventionally processed commercial 7075-T651 plate.

Application of Final Thermal Mechanical Treatment (FTMT) practices to 7475 plate produced strength/toughness relationships generally superior to that of 7075-T651 plate.



UNCLASSIFIED

FOREWORD

The Aluminum Company of America, Alcoa Technical Center, Alcoa Center, PA 15069, prepared this report to satisfy the requirements of U.S. Army Contract DAAA25-73-C-0657. The Alcoa personnel responsible for this program were Mr. J. E. Vrugink, principal investigator; Dr. B. K. Park, technical assistance in the area of microstructural interpretation; and Dr. R. E. Frishmuth, technical assistance in the area of notch sensitivity. The investigation was supervised by Messrs J. T. Staley and H. Y. Hunsicker. The Frankford Arsenal contract technical supervisor was Dr. Jeffrey Waldman and the Tank Automotive Research and Development Command Project Engineer was Mr. Harry Spiro.

[illegible]

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION-----	1
MATERIAL AND PROCEDURE-----	4
Alloy and Composition Selection-----	4
Ingot-----	4
Fabrication and Thermal Practices-----	5
ITMT-----	6
FTMT-----	9
Grain Size Determinations-----	9
Mechanical Property Determination-----	10
RESULTS AND DISCUSSION-----	10
ITMT of 7475 Plate-----	11
Grain Dimensions vs Fabrication Variables-----	11
Grain Structure vs Mechanical Properties-----	12
Mechanical Properties vs Grain Dimensions-----	14
Ductility and Toughness vs Microstructure-----	15
Summary - ITMT Processing of 7475 Plate-----	18
FTMT of 7475 Plate-----	19
ITMT of Al-Zn-Mg-Cr Plate-----	21
Fabrication of 7475 Plate for Ballistic Evaluation-----	21
CONCLUSIONS-----	22
REFERENCES-----	24
APPENDIX A-----	85
APPENDIX B-----	87
APPENDIX C-----	106
APPENDIX D-----	110
APPENDIX E-----	113
APPENDIX F-----	120
DISTRIBUTION LIST-----	168

LIST OF ILLUSTRATIONS

<u>No.</u>		<u>Page</u>
1	Sectioning of Cropped D.C. Ingots-----	50
2	Rolling Sections Used in ITMT Evaluation-----	51
3	Specimens Used in Evaluating Properties of 1.00" to 1.25" Thick 7475 and Al-Zn-Mg Alloy Plate-----	52
4	Specimens Used in Evaluating Properties of 1.50" to 2.50" Thick 7475 and Al-Zn-Mg Alloy Plate-----	53
5	Microstructure and Properties of S-427507 (AR+HR) 7475-T6 Plate-----	54
6	Microstructure and Properties of S-422622A (AR+HR) 7475-T6 Plate-----	55
7	Microstructure and Properties of S-422622B1 (AR+HR) 7475-T6 Plate-----	56
8	Microstructure and Properties of S-418967-50 (AR+HR) 7475-T6 Plate-----	57
9	Microstructure and Properties of S-422622G1 (AR+HR) 7475-T6 Plate-----	58
10	Microstructure and Properties of S-427506 (AR) 7475-T6 Plate-----	59
11	Microstructure and Properties of S-421675E61 (AR) 7475-T6 Plate-----	60
12	Microstructure and Properties of S-418967-40 (AR) 7475-T6 Plate-----	61
13	Microstructure and Properties of S-421675F3 (AR) 7475-T6 Plate-----	62
14	Microstructure and Properties of S-422622C2 (HR) 7475-T6 Plate-----	63
15	Microstructure and Properties of S-418967-30 (HR) 7475-T6 Plate-----	64
16	Microstructure and Properties of S-422622C1 (HR) 7475-T6 Plate-----	65
17	Effect of Warm Rolling Reductions on Grain Dimensions of 1.25"-1.50" Thick 7475-T6 Plate Using ITMT Practices-----	66
18	Effect of Warm Rolling Reductions on Grain Dimensions of 2.50" Thick 7475-T6 Plate Using ITMT Practices---	67
19	Longitudinal Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Yield Strength-----	68
20	Long-Transverse Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Yield Strength-----	69
21	Short-Transverse Properties of 2.50" Thick Plate as a Function of Yield Strength-----	70
22	Longitudinal Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in the Short-Transverse Direction-----	71
23	Long-Transverse Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in the Short-Transverse Direction-----	72

LIST OF ILLUSTRATIONS (CONTINUED)

<u>No.</u>		<u>Page</u>
24	Short-Transverse Properties of 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in the Short-Transverse Direction-----	73
25	Longitudinal Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in the Longitudinal Direction-----	74
26	Long-Transverse Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in The Longitudinal Direction-----	75
27	Short-Transverse Properties of 2.50" Thick 7475-T6 Plate as a Function of Grain Dimension in the Longitudinal Direction-----	76
28	Longitudinal Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Aspect Ratio of Grains-----	77
29	Long-Transverse Properties of 1.25" and 2.50" Thick 7475-T6 Plate as a Function of Aspect Ratio of Grains-----	78
30	Short-Transverse Properties of 2.50" Thick 7475-T6 Plate as a Function of Aspect Ratio of Grains-----	79
31	Properties of 1.50" Thick 7475-T6 Plate as a Function of Yield Strength-----	80
32	Effect of Amount of Cold Rolling on Long-Transverse Properties of 1.00" to 1.30" Thick 7475-T6X Plate Using FTMT Practices-----	81
33	NTS/YS Ratio-Yield Strength Relationship for 1.00" to 1.30" Thick 7475 Plate Processed Using FTMT Practices-----	82
34	Microstructure and Properties of S-422622-1 (AR+HR) 7475-T7X Plate for Ballistic Evaluation-----	83
35	Microstructure and Properties of S-422622-2 (AR+HR) 7475-FTMT Plate for Ballistic Evaluation-----	84
B1	Fabrication Details for Ingot Sections 421675A and 422014A-----	88
B2	Fabrication Details for Ingot Sections 421675B and 422014B-----	89
B3	Fabrication Details for Ingot Sections 421675C and 422014C-----	90
B4	Fabrication Details for Ingot Sections 421675D and 422014D-----	91
B5	Fabrication Details for Ingot Sections 421675E and 422014E-----	92
B6	Fabrication Details for Ingot Sections 421675F and 422014F-----	93

LIST OF ILLUSTRATIONS (CONTINUED)

<u>No.</u>		<u>Page</u>
B7	Fabrication Details for Ingot Sections 421675G and 422014G-----	94
B8	Fabrication Details for Ingot Sections 421675H and 422014H-----	95
B9	Fabrication Details for Ingot Sections 421675I and 422014I-----	96
B10	Fabrication Details for Ingot Sections 421675J and 422014J-----	97
B11	Fabrication Details for Ingot Sections 421675K and 422014K-----	98
B12	Fabrication Details for Ingot Sections 421675L and 422014L-----	99
B13	Fabrication Details for Ingot Sections 422622A and B--	100
B14	Fabrication Details for Ingot Section 422622C-----	101
B15	Fabrication Details for Ingot Sections 422622E and G--	102
B16	Procedures Used to Fabricate 1.50" Thick 7475-T6 Plate-----	103
B17	Procedures Used to Evaluate FTMT Practices on 1.25" Thick 7475 Plate-----	104
B18	Procedures Used to Fabricate 1.00" Thick Plate for Ballistic Evaluation-----	105
C1	Sharply Notched Round Tensile Specimen-----	107
C2	Sharply Notched 1/2" Dia. Notch-Tensile Specimen (Tapered Seat)-----	108
C3	Compact Tension Fracture Toughness Specimen-----	109
F1a	Micrographs (SEM) Showing Distribution of Particles in the Unrecrystallized Sample-----	134
F1b	Micrographs (SEM) Showing Distribution of Particles in the Recrystallized Sample-----	135
F1c	Micrographs (SEM) Showing Distribution of Particles in the Recrystallized Plus Hot Rolled Sample-----	136
F2a	Microstructure and Properties of S-418967-30 (HR) 7475-T6 Plate-----	137
F2b	Microstructure and Properties of S-418967-40 (AR) 7475-T6 Plate-----	138
F2c	Microstructure and Properties of S-418967-50 (AR+HR) 7475-T6 Plate-----	139
F3a	Micrograph (TEM) of Undeformed Unrecrystallized Material-----	140
F3b	Micrograph (TEM) of Undeformed Unrecrystallized Material-----	141
F4a	Micrograph (TEM) of Undeformed Recrystallized Material-----	142

LIST OF ILLUSTRATIONS (CONTINUED)

<u>No.</u>		<u>Page</u>
F4b	Micrograph (TEM) of Undeformed Recrystallized Material-----	143
F5	Micrograph (TEM) of Undeformed Recrystallized Material Plus Hot Rolled Material-----	144
F6a	Micrograph (TEM) Representing Uniformly Deformed Regions of Unrecrystallized Material-----	145
F6b	Micrograph (TEM) Representing Uniformly Deformed Regions of Unrecrystallized Material-----	146
F7a	Micrograph (TEM) Showing Uniformly Deformed Regions of Recrystallized Material-----	147
F7b	Micrograph (TEM) Showing Uniformly Deformed Regions of Recrystallized Material-----	148
F8a	Micrograph (TEM) Showing Uniformly Deformed Regions of Recrystallized Plus Hot Rolled Material-----	149
F8b	Micrograph (TEM) Showing Uniformly Deformed Regions of Recrystallized Plus Hot Rolled Material-----	150
F9a	Optical Micrograph Showing Slip Line Structure in Uniformly Deformed Region (L-T Plane) of Unrecrystallized Material-----	151
F9b	Optical Micrograph Showing Slip Line Structure in Necked Region (L-T Plane) of Unrecrystallized Material-----	152
F9c	Optical Micrograph Showing Fracture in L-N Plane of Unrecrystallized Material-----	153
F10a	Optical Micrograph Showing Slip Line Structure (L-T Plane) in the Uniformly Deformed Region of Recrystallized Material-----	154
F10b	Optical Micrograph Showing Slip Line Structure (L-T Plane) in Necked Region of Unrecrystallized Material-----	155
F10c	Optical Micrograph Showing Fracture in L-N Plane of Recrystallized Material-----	156
F11a	Optical Micrograph Showing Slip Line Structure (L-T Plane) in Uniformly Deformed Region of Recrystallized Plus Hot Rolled Material-----	157
F11b	Optical Micrograph Showing Slip Line Structure (L-T Plane) in Necked Region of Recrystallized Plus Hot Rolled Material-----	158
F11c	Optical Micrograph Showing Fracture in L-N Plane of Recrystallized Plus Hot Rolled Material-----	159
F12	Fractographs of Fracture Toughness Specimen (L-T) of Unrecrystallized Material-----	160
F13	Fractographs of Fracture Toughness Specimen (L-T) of Recrystallized Material-----	161
F14	Fractographs of Fracture Toughness Specimen (L-T) of Recrystallized Plus Hot Rolled Material-----	162

LIST OF ILLUSTRATIONS (CONTINUED)

<u>No.</u>		<u>Page</u>
F15	Fractographs of L Notched Tensile Specimen of Unrecrystallized Material-----	163
F16	Fractographs of L Notched Tensile Specimen of Recrystallized Material-----	164
F17	Fractographs of L Notched Tensile Specimen of Recrystallized Plus Hot Rolled Material-----	165
F18	Scanning Electron Fractographs of Fracture Toughness Specimens-----	166
F19	Scanning Electron Micrographs of Rapidly Quenched Samples-----	167

LIST OF TABLES

1	Fabrication of 1.25" and 2.50" Thick 7475-T6 Plate in Phase I-----	25
2	Fabrication of 1.25" and 2.50" Thick Al-Zn-Mg Alloy-T6 Plate in Phase I-----	26
3	Fabrication of 2.50" Thick 7475-T6 Plate in Phase II-----	27
4	Fabrication of 2.50" Thick Al-Zn-Mg Alloy-T6 Plate in Phase II-----	28
5	Fabrication of 1.25" and 2.50" Thick 7475-T6 Plate in Phase III-----	29
6	Fabrication of 1.50" Thick 7475-T6 Plate in Phase IV-----	30
7	Properties of 1.25" Thick Recrystallized Plus Hot Rolled 7475-T6 Plate-----	31
8	Properties of 1.25" Thick Recrystallized 7475-T6 Plate-----	32
9	Properties of 1.25" Thick Hot Rolled 7475-T6 Plate---	33
10	Properties of 1.50" Thick 7475-T6 Plate-----	34
11	Properties of 2.50" Thick Recrystallized Plus Hot Rolled 7475-T6 Plate-----	35
12	Properties of 2.50" Thick Recrystallized 7475-T6 Plate-----	36
13	Properties of 2.50" Thick Hot Rolled 7475-T6 Plate---	37
14	Properties of 1.25" Thick Recrystallized Plus Hot Rolled Al-Zn-Mg Alloy T6 Plate-----	39
15	Properties of 1.25" Thick Recrystallized Al-Zn-Mg Alloy T6 Plate-----	40
16	Properties of 2.50" Thick Recrystallized Plus Hot Rolled Al-Zn-Mg Alloy T6 Plate-----	41
17	Properties of 2.50" Thick Recrystallized Al-Zn-Mg Alloy T6 Plate-----	42

LIST OF TABLES (CONTINUED)

<u>No.</u>		<u>Page</u>
18	Properties of Al-Zn-Mg Alloy T6 Plate Produced By Hot Rolling-----	43
19	Grain Count, Grain Dimensions, and Fabricating Variables for ITMT Processed 7475-T6 Plate-----	45
20	Long-Transverse Properties of 7475 Plate Fabricated Using FTMT Treatments-----	47
21	Fabrication of 1.00" Thick 7475 Plate for Ballistic Evaluation by Frankford Arsenal-----	49
D1	Results of Multiple Linear Regression Analyses of Longitudinal Data for 7475-T6 Plate-----	111
E1	Results of Tensile and Notched Tensile Tests on 1.50" Thick 7475-T6 Plate-----	116
E2	Notched Tensile/Tensile Strength and K_Q Results, 1.50" Thick 7475-T6 Plate-----	117
E3	Results of Tensile and Notched Tensile Tests on 1.50" Thick 7475-T6 Plate-----	118
E4	Notched Tensile/Tensile Strength Ratio Based on True Stresses-----	119

INTRODUCTION

Medium strength, high toughness aluminum alloys have been widely used in armor plate applications due to their good resistance to kinetic energy impact rounds. Indications are that resistance to penetration is increased with increases in strength, but that the reduced toughness levels accompanying significant increases in strengths achieved by conventional alloying and fabrication are not sufficient to prevent plate cracking and shattering. To take advantage of the greater potential penetration resistance resulting from higher strengths, increases in the toughness level of the high-strength aluminum alloys are required.

The aluminum industry has made significant advances in increasing fracture toughness at high strength levels in 2XXX and 7XXX aircraft structure alloys, i.e., 2419, 2124, 2048, 7149, 7050, 7175, and 7475, by refining alloy chemistry and introducing special processing. The increase in fracture toughness by reduction or elimination of both soluble and insoluble constituents (second-phase particles) present in the alloy structure has been broadly successful, but further substantial improvements derived solely by changes in alloy chemistry for the basic alloy systems are not considered as offering a high probability of achievement at the present time. Moreover, ballistic evaluations of alloys of these types have shown no consistently significant improvement in ballistic performance over that afforded by the aluminum alloys presently used for armor plate. Consequently, a new approach is needed.

Modifications in the grain structure of high-strength alloys have shown promise as a way to develop improved combinations of strength and ductility.

Plate commercially available today of both standard and high toughness varieties of the 7XXX alloys, hot rolled to final gauge, has typically an unrecrystallized, highly elongated lamellar grain structure and has fracture toughness in the short-transverse direction which is lower than the fracture toughness in the longitudinal and long-transverse directions. Recently, DiRusso, et al,¹ and Waldman, et al,² developed novel processes specifically designed to produce a much finer controlled grain morphology in 7XXX alloy plate than is obtained with conventional processing. These processes, referred to as Intermediate Thermal Mechanical Treatments (ITMT), involve establishing preliminary structures amenable to recrystallization by applying appropriate thermal treatments prior to working at lower than conventional hot working temperatures (warm working).^{*} These treatments introduce a relatively high degree of strain hardening which promotes recrystallization to fine, relatively equiaxed grain structures during subsequent thermal treatment. The ITMT products can be utilized either in this as-recrystallized condition (AR) or after subsequent hot rolling to elongate the grains (AR+HR).

Properties reported by these investigators have been very promising. DiRusso, et al,¹ reported that 0.4-in. thick super

^{*}The processes employed by DiRusso (ISML-ITMT) and by Waldman (FA-ITMT) differ in the thermal practices prior to warm rolling.

purity (0.0013% Fe and 0.004% Si) 7075-T6 plate fabricated using ISML-ITMT processes exhibited higher longitudinal and long-transverse ductility and toughness and short-transverse stress-corrosion properties than were exhibited in conventionally produced super purity 7075-T6 plate of the same gauge. Waldman, et al,² using super purity (0.01% Fe and 0.01% Si) 7075 ingots fabricated 0.4 and 0.7-in. thick plate using FA-ITMT and conventional processes. The specially processed plate developed higher ductility as measured by reduction in area of long-transverse tensile specimens, and the reduction in area increased as the mean grain thickness decreased. Waldman, et al,³ also disclosed that 1.0-in. thick super purity (0.02% Fe and 0.02% Si) 7075 plate fabricated using FA-ITMT processes, both (AR) and (AR+HR), had higher fracture toughness in the longitudinal and long-transverse directions in the T6, T76, and T73 tempers than did commercially produced 7075 plate in similar tempers.

Another method for improving the strength-fracture toughness relationship of 7XXX alloys is the use of a combination of special thermal and mechanical treatments following solution heat treatment and quenching called Final Thermal Mechanical Treatment (FTMT). The FTMT procedures, which have been extensively investigated,^{1,4-8} involve generally a preage at an artificial aging temperature prior to mechanical working and a second artificial aging treatment following the mechanical working step.

The goals of this contract were to explore and develop industrially viable schedules for producing aluminum alloy plate with significantly improved plane strain fracture toughness at two target

yield strength levels, (a) 60 to 70 ksi, (b) 70 to 80 ksi. The approach was to use ITMT processes to develop two types of grain structure in 1.25-in. to 2.50-in. plate of high purity Al-Zn-Mg-Cr alloys with and without a Cu addition. One target structure was fine recrystallized grains (AR), the other was a hot worked, fine-grain structure that had recrystallized at an intermediate step (AR+HR). Unrecrystallized (HR) 7475 plate was produced for comparison with ITMT processed plate from the same ingot, and results are also compared with data on commercial 7475 and 7075 plate.

MATERIAL AND PROCEDURE

Alloy and Composition Selection

Alloy 7475 and an experimental Cu-free Al-Zn-Mg-Cr alloy were selected for the program. Alloy 7475 is a modification of 7075 that has the Fe, Si, and other impurity elements restricted to the lowest values that are considered to be commercially practical. The Cu-free Al-Zn-Mg-Cr alloy contained slightly more Zn and Mg than nominal 7475 so that it would develop strength comparable to that of 7475. It was included because Cu-free Al-Zn-Mg-Cr alloys are weldable. The Fe and Si contents of the experimental alloy were controlled to the same limits as those of the alloy 7475.

Ingot

Direct chill (D.C.) ingots, 12-in. x 38-in. x 100-in., were used for this program. The ingots were stress relieved at 575°F, cropped, scalped to a thickness of either 9.25 or 10-in., and sawed into rolling sections (Figure 1). The compositions of

the ingots were determined on analytical samples cast with the ingots:

<u>Alloy</u>	<u>S. Number</u>	<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Cr</u>	<u>Zn</u>	<u>Ti</u>
7475	418967	0.06	0.12	1.65	0.00	2.35	0.23	5.79	0.01
7475	421675	0.04	0.07	1.64	0.01	2.23	0.17	5.62	0.01
7475	422622A,B,C	0.07	0.05	1.70	0.02	2.40	0.18	5.80	0.00
Al-Zn-Mg-Cr	422014	0.04	0.06	0.00	0.00	2.51	0.22	6.47	0.00

Fabrication and Thermal Practices

In the previous ITMT investigations,^{1,2,3} thermal treatment temperatures conventional for 7075 and up to about 900°F were employed. Prior Alcoa investigations⁹ had demonstrated beneficial effects of higher temperature and 960°F was employed extensively in the present investigation for ingot preheat, intermediate recrystallization, and final solution treatments.* Salt baths were employed in the prior investigations; in the present case, all thermal treatments were performed in circulating air furnaces. Work reported in Appendix A showed that the warm rolled 7475 plate recrystallized at 960°F for up to 20 hours developed the same grain size as comparable samples recrystallized for one hour at 860°F, regardless of heating rate or furnace type. In various parts of the program, thermal treatments at 860°F were used to provide direct comparison of results at the two temperatures. The treatment variants that included 860°F heating corresponded to ISML-ITMT and FA-ITMT practices.

For comparison and control at various stages of the ITMT process development, sections of the same ingot used for special

*The use of 960°F thermal treatments on nonhomogeneous material requires a presoak at lower temperatures to eliminate eutectic-forming phases.

processing were fabricated by a completely hot rolling practice which produces an unrecrystallized structure (HR).

ITMT

The ITMT process development and evaluation proceeded in four phases, the principal variants of which were warm rolling temperature and reduction. These factors strongly affect roll pressures, susceptibility to cracking or alligatoring, and the recrystallized grain size, which should be as fine as possible. Since workability and grain size are favorably affected in opposite directions by these warm working variables, there is a trade-off relationship between commercial viability and the metallurgical structure objectives.

Phase I. Rolling schedules for 7475 and the experimental Cu-free alloy to produce final gauges of 1.25 and 2.50-inches involving combinations of hot (750°F) and warm (600°F) rolling were followed as detailed in Tables 1 and 2. Warm (600°F) rolling reductions of up to 75% were applied directly to ingot rolling sections and to previously hot rolled material. Recrystallization treatments (960°F) were applied either at final gauge (AR) or at an intermediate gauge followed by 50% hot rolling reduction (AR+HR). Grain count data for these materials are tabulated in the tables.

Phase II. In an effort to achieve finer grain structures, warm rolling temperatures from 500 to 575°F were used in the second phase (Tables 3 and 4). Difficulties with alligatoring were encountered in applying large warm rolling reductions directly to

non-beveled 7475 ingots at 500 and 550°F. Grain count data obtained with 7475 warm rolled at 575°F were not greatly different than those observed in the Phase I material.

Phase III. Practices employed are described in Table 5. To obtain reductions >65% by warm rolling at 500°F, the entry end of ingot rolling sections or of previously hot rolled slab were beveled by sawing (Figure 2) prior to warm rolling to prevent alligatoring. Using the beveled rolling pieces, reductions of 81 to 88% were successfully applied at 500°F to ingot sections and 75% (higher reductions not attempted because of final thickness requirements) to previously hot rolled material. Accordingly, items were rolled to final 1.25-inch gauge entirely at 500°F by Alcoa Laboratories (S. No. 422622E1) and by Frankford Arsenal (S. Nos. 427506 and 427507), the latter employing recrystallization and solution heat treating temperatures lower than 960°F in salt baths. Other sections were fabricated employing preliminary hot rolling followed by 75% warm (500°F) reductions and final recrystallization (HR-WR-AR) or intermediate recrystallization followed by 28% final hot rolling reduction (HR-WR-AR-HR).

Grain count data included in Table 5 show that much finer grain sizes were produced by application of the lower temperature (500°F) warm rolling operations preceding recrystallization treatment.

To assist in selection of the fabricating practices employed in the final phase to produce material for more complete evaluation, tensile, notched-tensile and fracture toughness data were obtained

from material produced in all three phases. This also served to extend the range of fabricating variables covered by the mechanical property evaluations.

Phase IV. The final phase was designed to provide more complete three direction mechanical property evaluation and unequivocal correlation of these properties with the different grain morphologies unconfounded with differences in composition or particle morphologies derived from thermal practice variations. Using three rolling sections cut from a single ingot, three rolling schedules were employed to produce hot rolled, unrecrystallized (HR); fine-grain recrystallized (AR); and fine-grain recrystallized plus hot rolled (AR+HR) plate. A final gauge of 1.5-inches was selected to provide for maximum warm rolling reduction consistent with use of reasonable ingot breakdown reduction by hot rolling with further allowance for final hot rolling. This gauge was the minimum that permits satisfactory short-transverse direction mechanical property evaluation.

Use of the same thermal treatments (960°F) throughout was intended to eliminate any differences in morphology of second-phase insoluble constituent particles and high temperature solid-state precipitate ($Al_{12}Mg_2Cr$ dispersoid). Fabricating practice details are summarized in Table 6. The ITMT practices produced fine grains.

Details of all the ITMT fabricating practices employed in the four phases are illustrated by flow charts in Figures B1 through B16 in Appendix B.

FTMT

After a review was made of the various FTMT practices described in the literature, an FTMT practice developed for 7475 sheet at Frankford Arsenal⁸ was selected for evaluation because it could be readily applied to 1.25-in. thick 7475 plate. The Frankford practice consisted of solution heat treatment, quenching, preaging 6 hrs at 220°F, cold rolling, and final artificial aging at 250°F. In the work reported here, 8-in. x 12-in. pieces of 1.25-in. thick 7475 plate having either a recrystallized plus hot rolled structure (S-422622A) or an unrecrystallized structure (S-422622C2) were used. The FTMT practice used consisted of solution heat treating at 960°F, cold water quenching, preaging 6 hrs at 220°F, cold rolling 10, 15, or 20%, and final artificial aging at 250°F for 8, 16, or 24 hrs. The fabricating details are given in Figure B17 in Appendix B.

Grain Size Determinations

The grain size was determined at the midplane of 1.00-in. to 2.50-in. thick plate from grain count measurements made microscopically using the linear intercept method. Materials produced in Phases I and II were examined only in the longitudinal/short-transverse plane, while measurements were made in this and in the long-transverse/short-transverse plane for most of the items produced in Phases III and IV.

Mechanical Property Determination

The location, number, and type of specimens used to determine the properties and grain size of the 7475 and Al-Zn-Mg-Cr alloy plate are described in Figures 3 and 4. The notched tensile and compact tension fracture toughness specimen configurations are shown in Figures C1, C2, and C3 of Appendix C. Notched tensile and fracture toughness tests could not be made in the short-transverse direction on samples of 1.00-in. to 1.25-in. thick plate because of specimen size limitations.

None of the candidate plane strain stress intensity fracture toughness test measurements, K_Q , were valid K_{IC} values because one or more of the criteria specified by ASTM E-399 were not met, i.e., specimens not thick enough, fatigue crack too short, or curvature of fatigue crack exceeded allowable variation. The criteria which were not met, however, were not far beyond the specified limits. Consequently, the K_Q values obtained are considered to be meaningful for comparing relative fracture toughness of the various samples of plate.

RESULTS AND DISCUSSION

The experimental alloy Al-Zn-Mg-Cr plate developed a duplex grain structure which was attributed to the presence of twin columnar grains in the ingot. When this structure was detected, additional fabrication of the experimental alloy plate was stopped, and efforts concentrated on developing the target recrystallized grain size in 7475 plate.

Grain counts and complete mechanical property data for both alloys are presented in Tables 7 through 18. All of the

mechanical property values reported are the arithmetic means of values determined in duplicate tests. In the following paragraphs the effects of ITMT fabrication practice on grain dimensions are discussed first, then the effects of grain structure on mechanical properties. The relationships between the grain dimensions and the ductility and toughness of recrystallized plate are examined next, followed by structure analysis of plate fabricated from pieces of a single ingot with no differences in thermal history during fabrication other than rolling temperature.

ITMT of 7475 Plate

Grain Dimensions vs Fabrication Variables. The ITMT fabricating practices used in this program were designed to evaluate more thoroughly than had been possible in previous investigations the merits of the nonconventional processing and to explore the possibility of developing a commercially viable ITMT process. They were not designed to optimize or survey completely the effects of individual fabricating variables in the ITMT process. Thus, the warm rolling temperatures, reductions during warm rolling, and reductions during the initial hot rolling of the ingot (ingot breakdown) at 750°F were not changed in a systematic fashion, so the individual effect of each fabricating variable on grain dimensions of the plate is difficult to determine.

The grain counts, average grain dimensions calculated from the grain counts, and the corresponding fabricating variables for the 7475-T6 plate are given in Table 19. Three dimensional photomicrographs at 100X of the various plates in T6 temper are included

as Figures 5 through 16. Figures 5 through 9 show the ITMT (AR+HR) recrystallized plus hot rolled structures, Figures 10 through 13 show the ITMT (AR) recrystallized structures, and Figures 14 through 16 show the structures of the (HR) unrecrystallized 7475-T6 plate fabricated by hot rolling only. The grain thickness, grain length, and aspect ratio (average grain dimension in the longitudinal direction divided by average grain dimension in the short-transverse direction) of the grains (Table 19) are plotted as functions of the reduction achieved during warm rolling in Figures 17 and 18. No exact relationship between the grain dimensions and the different fabricating variables could be established but the following indications with respect to the 1.25 and 1.50-in. plate were noted:

1. Increasing the reduction during warm rolling prior to the recrystallization treatment decreased the thickness of the recrystallized grains and had no consistent effect on their length.
2. The reduction by warm rolling required to obtain the desired small grain thickness and length was lower when the warm rolling was preceded by hot rolling at 750°F (ingot breakdown) than when the ingot was warm rolled immediately.

Hot rolling the ingot at 750°F followed by warm rolling 75% at 500°F produced the desired fine grain, recrystallized structure. Due to limitations on the thickness of the rolling sections, the desired degree of grain refinement was not obtained in the 2.50 in. thick plate.

Grain Structure vs Mechanical Properties. The tensile properties, notched tensile strength/yield strength ratios, and K_Q values obtained on the samples of 7475-T6 plate are presented in

detail for the 1.25-in. thickness in Tables 7 through 9 and for the 2.50-in. thickness in Tables 11 through 13.

Elongation, reduction in area, notched tensile strength/yield strength ratio, and K_Q values are plotted as functions of yield strength for each of the three test directions, longitudinal, long-transverse, and short-transverse, in Figures 19 through 21, respectively. Data for both plate gauges are included in Figures 19 and 20; only the thicker material can be used for the Figure 21 comparisons. Coded symbols distinguish between data for the two gauges, for the three major process variants, (AR+HR), (AR), and (HR), and for the two temperature variants (960°F), (860-900°F). Included in these figures are lines representing the upper and lower bounds of the previously determined relationships between the toughness- and ductility-related properties and the yield strength for commercially hot rolled plate of alloys 7475 and 7075 in T651, T7651, and T7351 tempers (gauge range 1.30 to 2.62-in.).

The data reveal several significant points:

1. The longitudinal and long-transverse yield strengths of the recrystallized (AR) 7475-T6 plate were slightly lower than those of either the unrecrystallized (HR) or the recrystallized plus hot rolled (AR+HR) material, while the short-transverse yield strength variations showed no systematic relation to the process variables.
2. The longitudinal and long-transverse ductilities (elongation and reduction in area values) of the recrystallized (AR) and the recrystallized plus hot rolled (AR+HR) material were generally higher than those of the unrecrystallized (HR) material.
3. The longitudinal and long-transverse NTS/YS ratios of the recrystallized plus hot rolled (AR+HR) and

the unrecrystallized (HR) plate lie within the band established for commercial hot rolled 7475 plate in the T651, T7651, and T7351 tempers, the K_Q values for the recrystallized plus hot rolled (AR+HR) plate are in the lower half of the band for commercial hot rolled 7475 plate, and the K_Q values for the unrecrystallized (HR) plate are in the upper half or above the band for commercial hot rolled 7475 plate.

4. The longitudinal and long-transverse fracture toughness (NTS/YS and K_Q values) of the recrystallized (AR) plate were generally below the band for commercial hot rolled 7475 plate in the T651, T7651, and T7351 tempers and above the band for commercial conventionally hot rolled 7075 plate in the T651, T7651, and T7351 tempers.

Mechanical Properties vs Grain Dimensions. The effect of grain dimensions on the properties of the samples of laboratory-fabricated 7475-T6 plate cannot be even speculatively determined from Figures 19 through 21. Because of the wide range of yield strengths and indications that the other mechanical properties were influenced by yield strength and plate thickness, an estimate of the effects of these variables, yield strength and plate thickness, on the longitudinal, long-transverse, and short-transverse elongation, reduction in area, notched tensile strength/yield strength ratio, and K_Q values was attempted using multiple regression analyses so that ductility and toughness could be compared on the basis of equivalent yield strength levels. Yield strength, plate thickness, Fe content, plate structure (AR, AR+HR, and HR), and grain dimensions were used as independent variables, and the coefficients determined by the regression analyses were used as estimates of the effect of each independent variable on a given property. The large change in the coefficient for yield strength, plate thickness, and Fe content, in some cases

from a negative to a positive value, with the selection of the independent variables representing plate structure and grain dimensions was unfortunate. This large change in coefficients is shown by the listing of the individual coefficients for the longitudinal properties in Table D1, Appendix D.

Because of the large variation in coefficients indicating the effect of yield strength, plate thickness, and Fe content on the ductility and toughness of the plate, the properties were not normalized. Thus, the elongation, reduction in area, notched tensile strength/yield strength ratios and K_Q values (Tables 7, 8, 11, and 12) are plotted as functions of grain thickness in Figures 22 through 24, of grain length in Figures 25 through 27, and of grain aspect ratio in Figures 28 through 30. The parameter of grain thickness used in Figures 22 through 24 was the same parameter used by Waldman² in plotting the data from 0.4-in. and 0.7-in. thick plate.

The plots in Figures 22 through 30 show no significant change in the longitudinal, long-transverse, or short-transverse elongation, notched tensile strength/yield strength ratio, or K_Q values for the plates having a recrystallized (AR) or a recrystallized plus hot rolled (AR+HR) structure with decreasing grain thickness, decreasing grain length or increasing grain aspect ratio. There is some indication that the reduction in area increases with decreasing grain size.

Ductility and Toughness vs Microstructure. The mechanical properties (Table 10) of the 1.50-in. thick 7475-T6 plate fabricated to develop a recrystallized structure (AR), a recrystallized plus

hot rolled structure (AR+HR), and an unrecrystallized structure (HR) are plotted as functions of yield strength for each testing direction in Figure 31. Also plotted in Figure 31 are bands (upper and lower bounds) showing the relationship between yield strength and notched tensile strength/yield strength ratio and K_{IC} values previously determined for commercially hot rolled 7475 plate. Comparison of these plots with Figures 19 through 21 show that the higher Fe content in the 1.50-in. thick plate in comparison to those in the 1.25-in. and 2.50-in. thick plate, i.e., 0.12% Fe in the former vs 0.05 to 0.07% Fe in the latter, produced lower notched tensile strength/yield strength ratios and K_Q values. The relationship between the notched tensile strength/yield strength ratios and K_Q values for the three different plate structures (AR, AR+HR, and HR) remained the same as noted in the other comparisons. In an effort to explain these results, analyses were made of smooth and notched tensile data (Appendix E) and a detailed microstructural examination was made on samples of the plate (Appendix F). The results of the analyses described in Appendix E indicated that the recrystallized structure was more notch sensitive than either the recrystallized plus hot rolled or the unrecrystallized structures. The results of the microstructural examinations showed that the fracture toughness increased as the proportion of intergranular fracture decreased. The relative proportion of the intergranular fracture was related to the population and size of large particles at the grain boundaries in addition to those effects attributable simply to grain boundary morphology, in

particular, the relative orientation/grain boundary area relationships normal to the direction of tension. Some of the particles present at the grain boundaries were identified as having originated by precipitation during quenching.

To reduce the amount of such precipitate at the grain boundaries, 0.6-in. dia. cylindrical blanks were machined from the three types of plate. The blanks were heat treated, quenched in cold water, aged to the T6 temper and machined to 0.357-in diameter smooth specimens and 0.500-in. diameter notched tensile specimens. Analysis of the smooth and notched tensile data from the more rapidly quenched reheat treated specimens showed that the notch tensile strengths of all three structures increased but that the recrystallized structure was still the most notch sensitive structure. Microscopic (TEM) examination of the rapidly quenched material showed a reduced number of precipitate particles at the grain boundaries in the recrystallized and the recrystallized plus hot rolled material, but particles identified as Al_7Cu_2Fe constituents were unaffected by the reheat treatment.

Analysis of the results of the microstructural examinations of samples from the plate heat treated at full thickness (Appendix F) indicated that differences in the dislocation substructures strongly affected the ductility and the fracture toughness. The recrystallized grain structure, which developed high ductility, was essentially free of dislocations in contrast with the unrecrystallized structure, which contained dislocations within subgrains and along cell walls. Dislocations generated during deformation of the

recrystallized structure interacted with the grain boundaries, however, and provided low resistance to coalescence of voids nucleated by fracture or decohesion of particles at the grain boundaries. The resultant low toughness, intergranular fracture was significantly different from the high toughness, transgranular dimpled rupture mechanism initiated by $Al_{12}Mg_2Cr$ dispersoids predominantly within the grains of the unrecrystallized material.

Summary - ITMT Processing of 7475 Plate

Rolling temperature and the amount of reduction were the main variable factors in the present investigation which were used to control the grain structure and resultant mechanical properties. For the 7475 plate, reductions of at least 75% at a temperature near 500°F produced a fine, relatively equiaxed grain structure (AR) containing few dislocations and a relatively large number of particles along the grain boundaries. Plate having this structure developed slightly lower strength, higher ductility (reduction of area in smooth tensile specimens), and lower fracture toughness (NTS/YS ratios and K_Q values) than unrecrystallized (HR) 7475 plate containing dislocations within subgrains and along cell walls. Hot rolling the recrystallized structure at 750°F produced a structure after solution heat treatment that consisted of elongated recrystallized grains containing polygonized cells. This structure developed strength comparable to that of the unrecrystallized material with better ductility, equal notch toughness, and somewhat lower fracture toughness (K_Q).

FTMT of 7475 Plate

The results of long-transverse tensile and notched tensile tests made of the samples of 1.00-in. to 1.16-in. thick 7475 plate given the various FTMT practices are summarized in Table XX. The thickness of the plate samples dictated use of only 0.5-in. diameter notched tensile specimens as a measure of toughness. Comparison of the notched tensile strength/yield strength ratios determined on the FTMT plates with ratios obtained on thicker 7475 plate tested using 1-1/16-in. diameter notched specimens required that the ratios obtained using 0.5-in. diameter notched specimens be converted to ratios expected from 1-1/16-in. diameter specimens. The ratios were converted using correlations established at Alcoa Laboratories.

In order to compare toughness over a range of yield strengths and provide for any differences in response to final artificial aging arising from possible prior strain effects on aging rate at 250°F, three aging times at this temperature were used, i.e., 8, 16, and 24 hours. There was no consistent change in yield strengths or notched tensile strength/yield strength ratios with increasing aging time at 250°F for the various amounts of cold rolling. Therefore, the yield strengths, reduction in area values, and notched tensile strength/yield strength ratios obtained for the three aging times were averaged for each amount of cold rolling.

The average, maximum and minimum yield strengths, reduction in area values, and notched tensile strength/yield strength ratios for the various samples of plates are plotted as functions of percent reduction applied during cold rolling in Figure 32 and as

functions of the yield strengths in Figure 33. Also included in Figure 33 are two bands, one representing the notched tensile strength/yield strength ratio versus yield strength relationship for commercially-hot rolled 7475 plate and the other for conventionally-processed commercial 7075 plate. The plots in Figure 32 show that the yield strength increases and the reduction in area and notched tensile strength/yield strength ratios decrease with increasing amount of cold work for plate having either an initially recrystallized plus hot rolled structure (AR+HR) or an unrecrystallized structure (HR). The yield strengths increased at a slightly higher initial rate and the notched tensile strength/yield strength ratios decreased at a slightly lower rate with increasing amounts of cold rolling for the unrecrystallized (HR) plate than for the recrystallized plus hot rolled (AR+HR) plate. The reduction in area values for the recrystallized plus hot rolled plate (AR+HR) were consistently higher than those for the unrecrystallized plate (HR).

The data in Figure 33 show that the use of FTMT practices produced yield strengths exceeding the expected range for either 7475 or 7075 in the T6 temper. The notched tensile strength/yield strength ratios of the FTMT material fall at and below a linear extrapolation of the lower edge of the band for commercially-hot rolled 7475-T6. The notch toughness of the FTMT-processed recrystallized plus hot rolled (AR+HR) material was somewhat lower than that of the FTMT-processed unrecrystallized (HR) material for a given yield strength.

The greater the amounts of cold rolling used, the closer the notch toughness approached that of 7075. The data indicated, however, that the use of FTMT practices on 7475 plate will produce an improvement in the strength-fracture toughness relationship over that which would be expected with similarly processed 7075 plate. Moreover, the data clearly indicate that recrystallized plus hot rolled (AR+HR) 7475 plate develops higher ductility than unrecrystallized (HR) 7475 plate when given a FTMT-type practice.

ITMT of Al-Zn-Mg-Cr Plate

Results of the mechanical property tests made on the samples of 1.25-in. and 2.50-in. thick Al-Zn-Mg-Cr alloy plate in the T6 temper (Tables 14 through 18) show that the Al-Zn-Mg-Cr alloy plate developed strengths that were comparable to those of the 7475-T6 plates and notched tensile strength/yield strength ratios that were substantially lower than those of 7475-T6.

Fabrication of 7475 Plate for Ballistic Evaluation

The results of the mechanical property tests and optical microscopic examinations made on the samples of 1.25-in. and 2.50-in. thick 7475-T6 and Al-Zn-Mg-Cr alloy T6 plate fabricated using ITMT practices and on 1.00-in. to 1.16-in. thick 7475 plate fabricated using FTMT practices were reviewed and discussed with personnel at Frankford Arsenal. As a result of these discussions, two practices were selected to be used in the fabrication of 1.00-in. thick 7475 plate for ballistic evaluation. These two practices are described in Table 21 and the details of the practices are given in Figure B18 in Appendix B of this report.

The first practice was designed to produce 1.00-in. thick plate having a fine grain, recrystallized plus hot rolled (AR+HR) structure and a long-transverse yield strength in the range of 60 to 70 ksi. The structure and strength were to be obtained by the use of an ITMT practice and overaging to a T7X temper. The second practice was designed to produce plate of the same thickness having a fine grain, recrystallized plus hot rolled (AR+HR) structure and a long-transverse yield strength in the range of 70 to 80 ksi. The structure and strength were to be obtained by combining an ITMT practice with an FTMT practice.

Thirty pieces 1.0-in. x 9-in. x 18-in. of 7475 plate were fabricated at Alcoa Laboratories using the first practice and thirty-eight pieces of the same dimensions using the second practice. These were supplied to Frankford Arsenal for ballistic evaluation.

Microstructures and tensile properties obtained on a sample of the plate fabricated by each practice are included as Figures 34 and 35. Fine grain, recrystallized structures were obtained in both plates and the long-transverse yield strengths were in the desired range.

CONCLUSIONS

The results of the work carried out under this contract showed the following:

1. An ITMT practice consisting of warm rolling at 500°F for a reduction of at least 75%, followed by a recrystallization treatment at 960°F, produced fine-grained, relatively equiaxed recrystallized structure (AR) in 7475 plate.

2. Alloy 7475-T6 plate having this recrystallized (AR) structure had slightly lower strengths and fracture toughness and higher ductility than laboratory or commercial 7475-T6 plate having an unrecrystallized (HR) structure.
3. Alloy 7475-T6 plate that was recrystallized to a fine-grain size, then hot rolled 25% at 750°F had strengths similar to, and ductility higher than either laboratory or commercial hot rolled unrecrystallized 7475-T6 plate and had fracture toughness similar to commercial hot rolled 7475-T6 plate but slightly lower than laboratory hot rolled 7475-T6 plate.
4. The lower toughness of the 7475-T6 plate having a recrystallized (AR) structure is attributed to a higher proportion of intergranular fracture.
5. Al-Zn-Mg-Cr (Cu-free) alloy plate in the T6 temper having either a recrystallized (AR) or a recrystallized plus hot rolled (AR+HR) structure had comparable strengths and lower toughness than 7475-T6 plate with the same structures.
6. FTMT practices applied to 7475 plate developed strength-toughness relationships generally superior to that of 7075-T6 plate.

REFERENCES

1. DiRusso, E., Conserva, M., Buratti, M., and Gatto, F., "A New Thermo-Mechanical Procedure for Improving the Ductility and Toughness of Al-Zn-Mg-Cu Alloys in the Transverse Direction," Materials Science and Engineering, 14(1974), 23-36.
2. Waldman, J., Sulinski, H., Markus, H., "New Processing Techniques for Aluminum Alloys," Metallurgical Transactions, 5, March 1974, 573-583.
3. U. S. Patent 3,847,681.
4. Thompson, D. S., Levy, S. A., Spänaler, G. E., and Benson, D. K., "Program to Improve the Fracture Toughness and Fatigue Resistance of Aluminum Sheet and Plate for Aircraft Applications," WPAFB Contract No. F33615-72-C-1202, Semi-Annual Report for the Period June 1, 1972, to December 31, 1972, January 1973.
5. DiRusso, E., Conserva, M., Gatto, F., and Markus, H., "Thermo-mechanical Treatments on High Strength Al-Zn-Mg(-Cu) Alloys," Met.Trans., 4, April 1973, 1133-1144.
6. Ostermann, F., "Improved Fatigue Resistance of Al-Zn-Mg-Cu (7075) Alloys Through Thermomechanical Processing," Met.Trans., 2, 1971, 2897-2902.
7. Ruch, L., and Sulinski, H. "Final Thermal Mechanical Treatment of 7039, 7075, X7007, and X7050 Alloys," Frankford Arsenal Report (Quoted in Reference 2).
8. George, H. P., "Metallurgical Advances for Aluminum Cartridge Case Application," Frankford Arsenal Report R-2081, 1973.
9. U. S. Patent 3,791,880.

TABLE 1

FABRICATION OF 1.25" AND 2.50" THICK 7475-T6 PLATE IN PHASE I

S. Number	Plate		10"x9"x21" Rolling Sections						Rolled Slab				Recrystal- lization		Rolling at 750°F Reduc- tion, %	Sol.HT Hrs/°F
	Grain Count, g/mm ²	Y C	Sect. Fab.	Thermal		Rolling		Thick, in.	Treat- ment	Temp, °F	Reduc- tion, %	Thick, in.	Thermal Treat- ment, Hrs/°F			
				Treat- ment	Temp, °F	Temp, °F	Reduc- tion, %									
1.25" Thick Plate																
421675A1	14	33	421675A	A	750	75	2.50	A	600	50	1.25	10/960	None	2/960		
421675B1			421675B	Hot Rolled												
421675C1	12	50	421675C	A	750	50	5.00	A	600	75	1.25	10/960	None	2/960		
421675D1	N.D.		421675D	B	600	75					2.50	10/960	50	2/960		
421675E1	8	20	421675E	A	750	50	5.00		600	50	2.50	10/960	50	2/960		
2.50" Thick Plate																
421675B3			421675B	Hot Rolled												
421675C3	8	12	421675C	A	750	50	5.00	A	600	50	2.50	10/960	None	2/960		
421675D3	14	20	421675D	B	600	75					2.50	10/960	None	2/960		
421675F3	5	24	421675F	B	600	50	5.00	B	600	50	2.50	10/960	None	2/960		
421675F1	N.D.		421675F	B	600	50					5.00	10/960	50	2/960		

Ingot Thermal Treatments "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

"B" - Heated 6 hrs at 860°F plus 20 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr and soaked at least 4 hrs at 650° or 500°F.

Slab Thermal Treatments "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr and soaked at least 4 hrs at 650° or 500°F.

"B" - Heated 10 hrs at 960°F, cooled to room temperature, heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr and soaked at least 4 hrs at 650° or 500°F.

All thermal treatments carried out in circulating air furnaces.

Plates cold water quenched after solution heat treatment and aged 24 hrs at 250°F at least 4 days after quenching.

Note: 1. Double recrystallization treatment.

BEST AVAILABLE COPY

TABLE 2

FABRICATION OF 1.25" AND 2.50" THICK Al-Zn-Mg ALLOY-T6 PLATE IN PHASE I

S. Number	Plate		10"x9"x20" Rolling Sections				Rolled Slab				Recrystal- lization		Rolling at 750°F	Sol.HT Hrs/°F	
	Grain Count, g/mm ²	Y Z	Sect. Fab.	Thermal Treat- ment	Rolling		Thick, in.	Thermal Treat- ment	Rolling		Thick, in.	Treat- ment, Hrs/°F			
					Temp, °F	Reduc- tion, %			Temp, °F	Reduc- tion, %					
422014A1	1	14	422014A	A	750	75	1.25" Thick Plate				1.25	10/960	None	2/960	
422014B1			422014B	Hot Rolled											
422014C1	10	33	422014C	A	750	50	5.00	A	600	75	1.25	10/960	None	2/960	
422014D1	N.D.		422014D	B	600	75	5.00	A	600	50	2.50	10/960	50	2/960	
422014E3	2	50	422014E	A	750	50	5.00	A	600	50	2.50	10/960	50	2/960	
							2.50" Thick Plate								
422014B3			422014B	Hot Rolled											
422014C3	2	5	422014C	A	750	50	5.00	A	600	50	2.50	10/960	None	2/960	
422014D3	5	14 ¹	422014D	B	600	75					2.50	10/960	None	2/960	
	1	3													
422014F3 ²	N.D.		422014F	B	600	50	5.00	B	600	50	2.50	10/960	None	2/960	
422014F1	N.D.		422014F	B	600	50					5.00	10/960	50	2/960	

Ingot Thermal Treatments "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

"B" - Heated 6 hrs at 860°F plus 20 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

Slab Thermal Treatments "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

"B" - Heated 10 hrs at 960°F, cooled to room temperature, heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

All thermal treatments carried out in circulating air furnaces. Plates cold water quenched after solution heat treatment and aged 24 hrs at 250°F at least 4 days after quenching.

Notes: 1. Duplex grain structure.

2. Double recrystallization treatment.

TABLE 3

FABRICATION OF 2.50" THICK 7475-T6 PLATE IN PHASE II

S. Number	Plate		10"x9"x20" Rolling Sections				Rolled Slab			Recrystallization		Rolling at 750°F Reduc- tion, %	Sol. HT, Hrs/°F
	Grain Count, g/mm ²	Y Z	Sect. Fab.	Thermal Treat- ment	Temp, °F	Rolling Reduc- tion, %	Thick, in.	Thermal Treat- ment	Temp, °F	Rolling Reduc- tion, %	Thick, in.	Thermal Treat- ment, Hrs/°F	
421675H	6	16	421675H	A	750°F	20	8.00	A	575	69	2.50	10/960	2/960
			421675I ¹	C	550	Alligatored at 4.3" (57% Reduction)							
421675J1	12	33	421675J	A	750	30	7.00	A	575	64	2.50	10/960	2/960
421675G1	6	12	421675G	B	575	65					3.50	10/960	2/960
421675J2	7	26	421675J	A	750	30	7.00	A	575	50	3.50	10/960	2/960
			421675K ²	D	500	Alligatored at 3.6" (64% Reduction)							
421675L1	5	20	421675L ²	D	500°F	65	Alligatored on Front End				3.50	10/860	2/860

Ingot Thermal Treatments "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

"B" - Heated 6 hrs at 860°F plus 20 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

"C" - Heated 18 hrs at 750°F, cooled to 575°F at 50°F/hr, and soaked at least 4 hrs at 575°F.

"D" - Heated 20 hrs at 860°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

Slab Thermal Treatments "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

All thermal treatments carried out in circulating air furnaces.

- Notes: 1. ISML-ITMT-type practice.
2. FA-ITMT-type practice.

TABLE 4

FABRICATION OF 2.50" THICK Al-Zn-Mg ALLOY-T6 PLATE IN PHASE II

S. Number	Plate		10"x9"x20" Rolling Sections						Rolled Slab			Recrystal- lization		Rolling at 750°F	Sol. HT Hrs/°F
	Grain Count, g/mm ²	Y Z	Sect. Fab.	Thermal Treat- ment	Rolling		Thick, in.	Thermal Treat- ment	Rolling Temp, °F	Reduc- tion, %	Thick, in.	Treat- ment, Hrs/°F			
					Temp, °F	Reduc- tion, %									
422014H	7	10	422014H	A	750	20	8.00	A	575	69	2.50	10/960	None	2/960	
422014J1	2	5	422014J	A	750	30	7.00	A	575	64	2.50	10/960	None	2/960	
422014L1	5	33	422014L ¹	D	500	75					2.50	10/860	None	2/860	
422014G1	1	33	422014G	B	575	65					3.50	10/960	28	2/960	
422014I	N.D.		422014I ²	C	575	57					4.30	10/860	42	2/860	
422014J2	N.D.		422014J	A	750	30	7.00	A	575	50	3.50	10/960	28	2/960	
422014K	5	14	422014K ¹	D	500	65					3.50	10/860	28	2/860	

Ingot Thermal Treatments "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

"B" - Heated 6 hrs at 860°F plus 20 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

"C" - Heated 18 hrs at 750°F, cooled to 575°F at 50°F/hr and soaked at least 4 hrs at 575°F.

"D" - Heated 20 hrs at 860°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

Slab Thermal Treatment "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650°F at 50°F/hr, and soaked at least 4 hrs at 650°F.

All thermal treatments carried out in circulating air furnaces.

- Notes: 1. FA-ITNT-type practice.
2. ISML-ITNT-type practice.

TABLE 5

FABRICATION OF 1.25" AND 2.50" THICK 7475-T6 PLATE IN PHASE III

S. Number	Plate		10"x9"x20" Rolling Sections						Rolled Slab				Recrystal- lization		Rolling at 750°F Reduc- tion, %	Sol. HT Hrs/°F
	Grain Count, g/mm ²	Y Z	Sect. Fab.	Thermal		Rolling		Thick, in.	Thermal Treat- ment	Temp, °F	Rolling Temp, °F	Thick, in.	Treat- ment, Hrs/°F			
				Treat- ment	Reduc- tion, %	Temp, °F	Reduc- tion, %									
1.25" Thick Plate																
421675E61	23	48	421675E	A	750	50	5.00	A	500	75	1.25	10/960	None	2/960		
422622E1	8	40	422622E	B	500	88					1.25	10/960	None	2/960		
427506 ²	12	61	422622	E	500	88					1.25	48/860 ¹	Ncne	2/900 ¹		
421675E51	10	38	421675E	A	750	50	5.00	A	500	67	1.75	10/960	28	2/960		
422622A	14	63	422622A	A	750	30	7.00	A	500	75	1.75	10/960	28	2/960		
422622B1	14	60	422622B	A	750	30	7.00	A	500	75	1.75	10/960	28	2/960		
422622B2	10	51	422622B	A	750	30	7.00	C	500	75	1.75	10/960	28	2/960		
422622C2			422622C	Hot Rolled												
422622E2	9	61	422622E	B	500	83					1.75	10/960	28	2/960		
427507 ²	8	52	422622	E	500	81					1.90	48/860 ¹	35	2/900 ¹		
2.50" Thick Plate																
422622C1			422622C	Hot Rolled												
422622G1	8	42	422622G	B	500	65					3.50	10/960	28	2/960		

Ingot Thermal Treatments "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

"B" - Heated 6 hrs at 860°F plus 20 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

"E" - Heated 48 hrs at 860°F, cooled to 775°F, soaked 5 hrs at 775°F, cooled to 500°F, soaked 4 hrs at 500°F. Treatments carried out in salt baths.

Slab Thermal Treatments "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr, and soaked at least 4 hrs at 650° or 500°F.

"C" - Heated 2 hrs at 960°F, furnace cooled to 500°F, and soaked at least 4 hrs at 500°F.

Unless otherwise noted, all thermal treatments carried out in circulating air furnaces. Plates cold water quenched after solution heat treatment and aged 24 hrs at 250°F at least 4 days after quenching.

Notes. 1. Thermal treatments carried out in salt baths.

2. FA-ITNT process.

TABLE 6

FABRICATION OF 1.50" THICK 7475-T6 PLATE IN PHASE IV

S. Number	Plate		9.25"x6"x22" Rolling Sections				Rolled Slab			Recrystallization			Rolling	
	Count, g/mm	Y Z	Sect. Fab.	Thermal Treatment	Temp, °F	Rolling Reduction, %	Thick, in.	Thermal Treatment	Temp, °F	Rolling Reduction, %	Thick, in.	Thermal Treatment, Hrs/°F	Rolling at 750°F Reduction, %	Sol. Hrs/°F
418967-30			418967	Hot Rolled										
418967-40	11	62	418967	A	750	35	6.0	A	500	75	1.50	18/960	None	2/960
418967-50	20	54	418967	A	750	14	8.0	A	500	75	2.00	18/960	25	2/960

Ingot Thermal Treatment "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.

Slab Thermal Treatment "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 650° or 500°F at 50°F/hr and soaked at least 4 hrs at 650° or 500°F.

All thermal treatments carried out in circulating air furnaces. Plates cold water quenched after solution heat treatment and aged 24 hrs at 250°F at least 4 days after quenching.

TABLE 7

PROPERTIES OF 1.25" THICK RECRYSTALLIZED PLUS HOT ROLLED 7475-T6 PLATE
(AR+HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				Grain Count				
			T.S.,		Y.S.,		El.,	R.A.,	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q ² ksi/in.	g/mm ³		
			ksi	%	ksi	%							X	Y	Z
421675D1	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
		T	77.4	64.6	16.8	28	97.3	1.26	1.51	N.D.					
		N	71.8	62.2	12.0	N.D.	N.D.	N.D.	N.D.	N.D.					
421675E1	960	L	77.6	68.7	17.1	32	101.9	1.31	1.48	41.5	N.D.	8	20	N.D.	
		T	77.8	68.9	16.4	26	96.3	1.24	1.40	37.8					
		N	71.8	62.2	12.0	N.D.	N.D.	N.D.	N.D.	N.D.					
421675E1	960	L	77.8	67.7	17.8	33	101.9	1.31	1.51	45.7	16	10	38	6080	
		T	77.5	67.2	17.1	30	94.4	1.22	1.40	38.4					
		N	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.					
422622A	960	L	83.2	73.6	16.7	37	100.8	1.21	1.37	33.2	21	14	63	18522	
		T	80.1	70.0	17.1	31	91.0	1.14	1.30	30.6					
		N	80.5	70.0	14.0	N.D.	N.D.	N.D.	N.D.	N.D.					
422622B1	960	L	83.8	73.4	16.4	21	98.9	1.18	1.57	42.6	22	14	60	18480	
		T	82.4	72.0	13.6	27	98.2	1.19	1.36	32.4					
		N	79.5	67.9	13.0	N.D.	N.D.	N.D.	N.D.	N.D.					
422622B2	960	L	82.6	73.0	16.0	24	101.2	1.23	1.39	N.D.	17	10	51	8670	
		T	80.7	70.7	14.3	28	97.0	1.20	1.37	N.D.					
		N	79.5	67.9	13.0	N.D.	N.D.	N.D.	N.D.	N.D.					
422622E2	960	L	82.0	72.3	17.5	28	96.9	1.18	1.34	N.D.	18	9	61	9882	
		T	80.1	69.7	16.0	33	88.8	1.11	1.27	N.D.					
		N	78.4	68.1	13.0	N.D.	N.D.	N.D.	N.D.	N.D.					
4275073	900	L	80.4	70.4	16.1	24	96.2	1.20	1.37	38.6	13	8	52	5408	
		T	78.9	68.7	14.6	24	81.5	1.03	1.19	30.1					
		N	78.8	69.6	8.0	N.D.	N.D.	N.D.	N.D.	N.D.					

TABLE 8

PROPERTIES OF 1.25" THICK RECRYSTALLIZED 7475-T6 PLATE
(AR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				N.T.S., ¹ ksi	Toughness			Grain Count					
			T.S., ksi	Y.S., ksi	El., %	R.A., %		NTS/TS	NTS/YS	K _Q ² ksi/in.	g/mm		g/mm ³			
											X	Y	Z	X	Y	Z
421675A1	960	L	74.5	65.0	19.0	35	97.0	1.30	1.49	35.7	N.D.	14	33	N.D.		
		T	76.7	66.4	17.1	24	89.3	1.16	1.34	32.4						
		N	73.1	62.9	12.0	N.D.	N.D.	N.D.	N.D.	N.D.						
421675C1	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	12	50	N.D.		
		T	76.4	64.4	17.1	30	89.1	1.17	1.38	N.D.						
		N	73.2	62.6	11.0	N.D.	N.D.	N.D.	N.D.	N.D.						
421675E61	960	L	75.2	64.8	19.6	40	95.7	1.27	1.48	40.2	30	23	48	33120		
		T	77.1	66.3	17.1	30	84.7	1.10	1.28	32.2						
		N	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.						
422622E1	960	L	78.2	67.9	17.5	33	90.6	1.16	1.33	N.D.	12	8	48	3840		
		T	78.9	67.7	16.7	27	86.8	1.10	1.28	N.D.						
		N	78.3	67.9	12.0	N.D.	N.D.	N.D.	N.D.	N.D.						
427506 ³	900	L	78.5	68.6	19.3	40	95.0	1.21	1.38	33.6	18	12	61	13176		
		T	78.7	67.8	17.1	32	84.0	1.07	1.24	29.3						
		N	80.9	71.1	14.0	N.D.	N.D.	N.D.	N.D.	N.D.						

TABLE 9

PROPERTIES OF 1.25" THICK HOT ROLLED 7475-T6 PLATE

(HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				Grain Count					
			T.S.,		Y.S.,		El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _{IC} ksi/in.	g/mm ³			
			ksi	ksi	g/mm	X							Y	Z	XYZ	
421675B1	960	L	76.4	67.8	17.9	32	100.2	1.31	1.48	49.0						
		T	77.2	67.5	15.7	24	92.0	1.19	1.36	39.7						
		N	72.8	63.8	8.0	N.D.	N.D.	N.D.	N.D.	N.D.						
422622C2	960	L	83.7	74.0	13.2	17	99.3	1.19	1.34	49.9						
		T	80.4	70.7	10.7	12	92.8	1.15	1.31	43.1						
		N	76.1	65.9	9.0	N.D.	N.D.	N.D.	N.D.	N.D.						

TABLE 10

PROPERTIES OF 1.50" THICK 7475-T6 PLATE

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				g/mm ³								
			T.S., ksi		Y.S., ksi		El., %		R.A., %		N.T.S., ¹ ksi		K _Q ² ksi/in.		g/mm				
															X	Y	Z		
418967-50	960	L	82.1	70.6	17.1	28	97.1	1.18	1.38	29.9	24	11	62	16368					
		T	80.5	69.0	15.0	25	84.7	1.05	1.23	29.2									
		N	79.3	66.3	12.0	N.D.	79.2	1.00	1.19	29.0									
		Recrystallized Plus Hot Rolled (AR+HR)																	
418967-40	960	L	79.3	67.7	17.9	32	90.1	1.14	1.33	32.4	22	20	54	23760					
		T	80.2	68.5	15.7	22	82.1	1.02	1.20	27.5									
		N	79.3	67.4	8.0	N.D.	85.0	1.07	1.26	23.6									
		Recrystallized (AR)																	
418967-30	960	L	83.8	73.0	15.0	19	99.8	1.19	1.37	40.9									
		T	81.3	70.3	15.7	21	90.0	1.11	1.28	32.6									
		N	81.4	67.1	10.0	N.D.	85.3	1.05	1.28	31.0									
		Hot Rolled (HR)																	

TABLE 11

PROPERTIES OF 2.50" THICK RECRYSTALLIZED PLUS HOT ROLLED 7475-T6 PLATE
(AR+HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				Grain Count			
			T.S., ksi	Y.S., ksi	El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q ² ksi in.	X	g/mm	Y	Z
421675F1	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	44.8	N.D.	N.D.	N.D.	N.D.
		T	77.3	66.7	14.3	23	82.3	1.06	1.23	N.D.				
		N	77.0	65.6	10.0	18	92.5	1.20	1.41	58.0				
421675J2	960	L	76.2	66.2	17.5	26	95.5	1.25	1.44	N.D.	8	7	26	1456
		T	75.5	64.8	16.4	24	85.6	1.13	1.32	N.D.				
		N	75.4	62.6	8.0	N.D.	91.2	1.21	1.46	N.D.				
421675G1	960	L	77.2	67.4	18.2	29	93.3	1.21	1.38	N.D.	N.D.	6	12	N.D.
		T	76.2	65.2	16.4	24	83.4	1.09	1.28	N.D.				
		N	69.6	61.6	4.0	N.D.	83.2	1.20	1.35	N.D.				
421675L1	860	L	76.7	67.0	15.4	26	93.4	1.22	1.39	N.D.	N.D.	5	20	N.D.
		T	74.7	64.8	12.2	14	74.2	0.99	1.15	N.D.				
		N	68.4	57.6	7.0	N.D.	75.6	1.11	1.31	N.D.				
422622G1	960	L	79.2	68.6	20.7	27	92.0	1.16	1.34	N.D.	14	8	42	4704
		T	78.6	67.4	14.3	28	84.8	1.08	1.26	N.D.				
		N	77.7	65.2	13.0	N.D.	92.7	1.19	1.42	N.D.				

TABLE 12

PROPERTIES OF 2.50" THICK RECRYSTALLIZED 7475-T6 PLATE
(AR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness			Grain Count			
			T.S., ksi	Y.S., ksi	El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q ² ksi/in.	X	Y	Z
421675C3	960	L	74.4	63.8	16.4	32	87.6	1.18	1.37	39.1	N.D.	8	12
		T	75.0	64.6	16.4	22	78.4	1.05	1.21	N.D.			
		N	77.4	65.7	9.0	20	88.9	1.15	1.35	46.4			
421675D3	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	14	20
		T	74.5	63.0	15.7	24	79.0	1.06	1.25	N.D.			
		N	76.4	66.0	8.0	12	86.6	1.13	1.31	N.D.			
421675F3	960	L	75.9	65.2	17.1	28	84.3	1.11	1.29	N.D.	9	5	24
		T	75.4	64.8	16.4	24	79.0	1.05	1.22	N.D.			
		N	76.2	63.3	12.0	N.D.	91.2	1.20	1.44	N.D.			
421675J1	960	L	73.5	63.6	19.0	34	86.0	1.17	1.35	N.D.	N.D.	12	33
		T	75.0	64.2	15.4	20	75.6	1.01	1.18	N.D.			
		N	69.8	56.6	10.0	N.D.	83.2	1.19	1.47	N.D.			
421675H	960	L	74.2	64.0	18.6	32	84.6	1.14	1.32	N.D.	N.D.	6	16
		T	75.3	64.3	13.6	19	80.1	1.06	1.25	N.D.			
		N	76.7	63.0	12.0	N.D.	89.6	1.17	1.42	N.D.			

TABLE 13

PROPERTIES OF 2.50" THICK HOT ROLLED 7475-T6 PLATE
(HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				Grain Count				
			T.S.,		Y.S.,		El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/Y _S	K _Q ² ksi/in.	g/mm		g/mm ³ XYZ
			ksi	ksi	X	Y							Z		
421675B3	960	L	81.8	71.7	13.6	18	101.2	1.24	1.43	56.6					
		T	78.4	66.7	11.4	14	87.4	1.11	1.31	N.D.					
		N	77.2	65.8	8.0	15	93.0	1.20	1.41	56.5					
422622C1	960	L	83.9	74.4	11.0	12	98.6	1.18	1.33	N.D.					
		T	76.5	67.8	5.7	8	94.0	1.23	1.39	N.D.					
		N	73.0	60.2	10.0	N.D.	94.2	1.29	1.56	N.D.					

NOTES FOR TABLES 7 THROUGH 13

S. Number	Composition							
	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti
421675	0.04	0.07	1.64	0.01	2.23	0.17	5.62	0.01
422622, 427506, 427507	0.07	0.05	1.70	0.02	2.40	0.18	5.80	0.00
418967	0.06	0.12	1.65	0.00	2.35	0.23	5.79	0.01

Unless otherwise noted, all thermal treatments carried out using circulating air furnaces.

Plate cold water quenched after solution heat treatment and aged 24 hrs at 250°F four days after quenching.

0.375" dia. tapered seat tensile specimens used for longitudinal and long-transverse tests, 0.125" dia. and 0.250" dia. tapered seat tensile specimens used for short-transverse tests.

Duplicate tests carried out on all plate samples with exception of 1.50" thick plates, S-418967-30, 40 and 50, where only single tests made.

Yield Strength = 0.2% offset.

M.T. No. C90573-D

1. 1-1/16" dia. threaded end notched tensile specimens used for longitudinal and long-transverse tests, 0.500" dia. tapered seat notch tensile specimens used for short-transverse tests.
2. K_Q values used because the values were not valid K_{Ic} values, but the K_Q values are meaningful. 1.00" thick compact tension fracture toughness specimens used for longitudinal and long-transverse tests, 0.50" thick compact tension fracture toughness specimens used for short-transverse tests.
3. Plate fabricated by Frankford Arsenal using 7475 ingot sections provided by Alcoa. All thermal treatments carried out in salt baths.

TABLE 14

PROPERTIES OF 1.25" THICK RECRYSTALLIZED PLUS HOT ROLLED Al-Zn-Mg ALLOY T6 PLATE
(AR+HR)

S. Number	Temp, °F	Test Dir.	Tensile				Toughness				Grain Count		
			T.S., ksi	Y.S., ksi	El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q , ² ksi/in.	X g/mm	Y g/mm	Z g/mm ³ XYZ
422014D1	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
		T	77.4	71.6	12.9	31	79.0	1.02	1.10	N.D.			
		N	73.7	66.4	10.0	N.D.	N.D.	N.D.	N.D.	N.D.			
422014E3	960	L	79.5	74.9	11.4	21	85.2	1.07	1.15	43.7	N.D.	2	50
		T	77.3	71.9	11.4	27	68.6	0.89	0.95	28.0			
		N	74.0	67.1	12.0	N.D.	N.D.	N.D.	N.D.	N.D.			

TABLE 15

PROPERTIES OF 1.25" THICK RECRYSTALLIZED Al-Zn-Mg ALLOY T6 PLATE
(AR)

S. Number	SHT Temp, °F	Test Dir.	Tensile				Toughness				Grain Count			
			T.S., ksi	Y.S., ksi	El., %	R.A., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _{IC} ² ksi/in.	X	Y	Z	g/mm ³ XYZ
422014A1	960	T	74.9	69.0	8.6	13	52.9	0.71	0.77	N.D.	N.D.	1	14	N.D.
		N	71.6	64.4	5.0	N.D.	N.D.	N.D.	N.D.	N.D.				
422014C1	960	T	75.0	68.9	13.2	23	56.5	0.75	0.82	N.D.	N.D.	10	33	N.D.
		N	73.4	66.6	8.0	N.D.	N.D.	N.D.	N.D.	N.D.				

TABLE 16

PROPERTIES OF 2.50" THICK RECRYSTALLIZED PLUS HOT ROLLED AL-Zn-Mg ALLOY T6 PLATE
(AR+HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile			R.A., %	Toughness			Grain Count		
			T.S., ksi	Y.S., ksi	El., %		N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q , ² ksi/in.	X	g/mm ³ XYZ
422014F1	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.
		T	76.5	70.4	7.1	9	64.3	0.84	0.91	N.D.	N.D.	N.D.
		N	74.6	68.4	5.0	9	84.8	1.14	1.24	N.D.	N.D.	N.D.
422014G1	960	L	76.9	71.7	11.8	17	77.4	1.01	1.08	N.D.	N.D.	N.D.
		T	76.2	69.6	11.8	18	60.6	0.80	0.87	N.D.	N.D.	N.D.
		N	75.9	67.6	9.0	N.D.	61.3	0.81	0.91	N.D.	N.D.	N.D.
422014I1	860	L	80.3	75.8	10.0	11	90.5	1.13	1.19	N.D.	N.D.	N.D.
		T	75.3	71.4	4.0	6	69.4	0.92	0.97	N.D.	N.D.	N.D.
		N	66.8	63.0	2.0	N.D.	69.7	1.04	1.11	N.D.	N.D.	N.D.
422014J2	960	L	75.5	70.6	14.0	24	80.8	1.07	1.14	N.D.	N.D.	N.D.
		T	75.4	69.8	7.9	17	67.4	0.89	0.97	N.D.	N.D.	N.D.
		N	77.2	68.0	11.0	N.D.	82.2	1.06	1.21	N.D.	N.D.	N.D.
422014K1	860	L	78.4	73.0	12.5	16	86.2	1.10	1.18	N.D.	N.D.	N.D.
		T	76.8	70.5	8.9	15	68.0	0.89	0.96	N.D.	N.D.	N.D.
		N	75.8	67.9	10.0	N.D.	83.8	1.11	1.23	N.D.	N.D.	N.D.

TABLE 17

PROPERTIES OF 2.50" THICK RECRYSTALLIZED AL-Zn-Mg ALLOY T6 PLATE
(AR)

S. Number	SHT Temp, °F	Test Dir.	Tensile			R.A., %	Toughness				Grain Count		
			T.S., ksi	Y.S., ksi	El., %		N.T.S., ¹ ksi	NTS/TS	NTS/YS	K _Q , ² ksi/in.	X	Y	Z
422014C3	960	L	73.4	67.4	15.0	28	59.8	0.81	0.89	35.0	N.D.	2	5
		T	74.4	67.4	10.0	16	59.3	0.80	0.88	N.D.			
		N	76.5	69.7	5.5	10	64.1	0.84	0.92	33.0			
422014D3	960	L	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	5	14 ³
		T	74.9	67.7	9.7	12	52.5	0.70	0.78	N.D.	1		3 ³
		N	76.9	70.4	4.0	6	61.5	0.80	0.87	N.D.			
422014F3	960	L	72.6	67.6	13.6	24	65.1	0.90	0.96	N.D.	N.D.	N.D.	N.D.
		T	73.6	67.5	10.7	24	53.2	0.72	0.79	N.D.			
		N	76.8	68.4	9.0	N.D.	58.0	0.76	0.85	N.D.			
422014H	960	L	73.0	67.8	13.9	24	62.8	0.88	0.93	N.D.	N.D.	7	10 ³
		T	74.9	69.0	7.5	14	53.9	0.72	0.78	N.D.	2		5 ³
		N	78.2	69.2	6.0	N.D.	68.9	0.88	1.00	N.D.			
422014J1	960	L	72.6	67.7	15.0	28	63.8	0.88	0.94	N.D.	N.D.	N.D.	N.D.
		T	75.4	70.2	6.4	10	59.0	0.78	0.84	N.D.			
		N	65.9	62.5	2.0	N.D.	57.1	0.87	0.92	N.D.			
422014L1	860	L	73.9	67.9	15.4	28	68.1	0.92	1.00	N.D.	N.D.	5	33 ³
		T	74.9	68.2	12.5	22	57.5	0.77	0.84	N.D.	5		14 ³
		N	76.3	69.6	10.0	N.D.	78.1	1.02	1.12	N.D.			

TABLE 18

PROPERTIES OF Al-Zn-Mg ALLOY T6 PLATE PRODUCED BY HOT ROLLING
(HR)

S. Number	SHT Temp, °F	Test Dir.	Tensile			Toughness			Grain Count				
			T.S., ksi	Y.S., ksi	El., %	N.T.S., ¹ ksi	NTS/TS	NTS/YS	g/mm ³				
			R.A., %	X	Y				Z				
			K _Q , ² ksi/in.	XYZ									
422014B3	960	T	73.0	70.0	3.6	6	71.3	0.98	1.02	N.D.			
			75.0	68.9	4.0	4	76.6	1.02	1.11	N.D.			
		N	<u>2.50" Thick Plate</u>										
422014B1	960	T	78.3	74.4	6.5	10	71.9	0.92	0.97	N.D.			
			73.4	65.2	5.0	N.D.	N.D.	N.D.	N.D.	N.D.			
		N	<u>1.25" Thick Plate</u>										

NOTES FOR TABLES 14 THROUGH 18

S. Number	Composition					
	Si	Fe	Cu	Mn	Mg	Ti
422014	0.04	0.06	0.00	0.00	2.51	0.00
					0.22	6.47
						0.00

All thermal treatments carried out using circulating air furnaces.

Plate cold water quenched after solution heat treatment and aged 24 hrs at 250°F four days after quenching.

0.357" dia. tapered seat tensile specimens used for longitudinal and long-transverse tests, 0.125" dia. and 0.250" dia. tapered seat tensile specimens used for short-transverse tests.

Duplicate tests carried out on all plate samples.

Yield Strength = 0.2% offset.

M.T. No. 090573-D

1. 1-1/16" dia. threaded end notched tensile specimens used for longitudinal and long-transverse tests, 0.500" dia. tapered seat notch tensile specimens used for short-transverse tests.
2. K_Q values used because the values were not valid K_{IC} values, but the K_Q values are meaningful. 1.00" thick compact tension fracture toughness specimens used for longitudinal and long-transverse tests, 0.50" thick compact tension fracture toughness specimens used for short-transverse tests.
3. Duplex grain structure.

TABLE 19

GRAIN COUNT, GRAIN DIMENSIONS, AND FABRICATING VARIABLES FOR ITWT PROCESSED 7475-T6 PLATE
(AR+HR)

Warm Rolling Reduction, %	Temp, °F	Rolling at 750°F After Recrystallization Reduction, %	Ingot Breakdown at 750°F Reduction, %	Recrystallization Temp, °F	Grain Count				Grain Dimensions				S. Number
					Z	Y	X	g/mm ³	Thick, mm	Length, mm	Aspect Ratio, Z/Y		
					Z	Y	X	g/mm ³	1/Z	1/Y	Z/Y		
1.25" thick Plate Having Recrystallized plus Hot Rolled Structure													
83	500	28	None	960	61	9	18	9882	0.016	0.111	6.778	422622E2	
81	500	35	None	860	52	8	13	5408	0.019	0.125	6.500	427507	
75	500	28	30	960	63	14	21	18522	0.016	0.071	4.500	422622A	
75	500	28	30	960	60	14	22	18480	0.017	0.071	4.286	422622B1	
75	500	28	30	960	51	10	17	8670	0.020	0.100	5.100	422622B2	
67	500	28	50	960	38	10	16	6080	0.026	0.100	3.80	421675E1	
50	600	50	50	960	20	8	ND	---	0.050	0.125	2.500	421675E1	
1.50" thick Plate Having Recrystallized plus Hot Rolled Structure													
75	500	25	14	960	62	11	24	16,368	0.016	0.090	5.636	418967-50	
2.50" thick Plate Having Recrystallized plus Hot Rolled Structure													
65	500	28	None	960	42	8	14	4704	0.024	0.125	5.250	422622G1	
65	500	28	None	860	20	5	ND	---	0.050	0.200	4.000	421675L1	
65	575	28	None	960	12	6	ND	---	0.083	0.167	2.00	421675G1	
50	575	28	30	960	26	7	8	1456	0.038	0.143	3.714	421675J2	

TABLE 19 (CONTINUED)

GRAIN COUNT, GRAIN DIMENSIONS, AND FABRICATING VARIABLES FOR ITMT PROCESSED 7475-T6 PLATE
(AR)

Warm Rolling Reduction, %	Temp, °F	Rolling at 750°F After Recrystallization Reduction, %	Ingot Breakdown at 750°F Reduction, %	Recrystal- lization Temp, °F	Grain Count			Grain Dimensions			S. Number
					g/mm			Thick, mm	Length, mm	Aspect Ratio, Z/Y	
					Z	Y	X	1/Z	1/Y	Z/Y	
<u>1.25" thick Plate Having Recrystallized Structure</u>											
88	500	None	None	860	61	12	18	0.016	0.083	5.083	427506
88	500	None	None	960	48	8	12	0.021	0.125	6.000	422622E1
75	500	None	50	960	48	23	30	0.021	0.043	2.087	421675E61
75	600	None	50	960	50	12	ND	0.020	0.083	4.167	421675C1
50	600	None	75	960	33	14	ND	0.030	0.071	2.357	421675A1
<u>1.50" thick Plate Having Recrystallized Structure</u>											
75	500	None	35	960	54	20	22	0.019	0.050	2.700	418967-40
<u>2.50" thick Plate Having Recrystallized Structure</u>											
69	575	None	20	960	16	6	ND	0.062	0.167	2.667	421675H
64	575	None	30	960	33	12	ND	0.030	0.083	2.750	421675J1
75	600	None	None	960	20	14	ND	0.050	0.071	1.429	421675D3
50	600	None	50	960	12	8	ND	0.083	0.125	1.500	421675C3
50	600 ¹	None	None	960	24	5	9	0.042	0.200	4.800	421675F3

Note: 1. Double recrystallization treatment.

TABLE 20

LONG-TRANSVERSE PROPERTIES OF 7475 PLATE FABRICATED USING FMT TREATMENTS

Percent Cold Work	Aging After Cold Work, hrs/°F	T.S.,		Y.S.,		El.,		R.A.,		0.50"Ø Specimen ²		1-1/16"Ø Specimen ¹	
		ksi	ksi	ksi	ksi	%	%	%	%	N.T.S., ksi	NTS/YS	N.T.S., ksi	NTS/YS
S-422622A - 7475 Plate Having a Recrystallized plus Hot Rolled Structure ³ (AR+HR)													
0	24/250	80.1	70.0	17.1	31					91.0	1.30		
10.5	8/250	85.9	77.4	12.0	28	105.7	1.37					1.11	
	16/250	86.1	77.4	12.5	23	101.1	1.31					1.02	
	24/250	86.8	78.5	12.0	25	110.3	1.41					1.18	
			77.8		25							1.10	
16.4	8/250	88.0	80.1	11.5	25	104.7	1.31					1.02	
	16/250	88.5	80.6	10.5	26	103.7	1.29					1.00	
	24/250	87.7	80.3	11.5	24	102.1	1.27					0.97	
			80.3		25							1.00	
22.6	8/250	89.9	82.6	11.0	23	96.5	1.17					0.81	
	16/250	89.3	82.8	10.0	24	97.5	1.18					0.82	
	24/250	88.8	82.6	9.5	26	94.5	1.14					0.79	
			82.7		24							0.81	
S-422622C2 - Hot Rolled 7475 Plate ² (HR)													
0	24/250	80.4	70.7	10.7	12					92.8	1.31		
9.5	8/250	87.2	78.4	7.5	11								
	16/250	87.6	79.9	5.5	6	110.8	1.39					1.15	
	24/250	88.1	79.4	9.0	11	112.4	1.42					1.20	
			79.6		9							1.18	
14.7	8/250	89.6	81.3	8.0	9	109.3	1.34					1.07	
	16/250	89.4	82.0	8.0	10	111.6	1.36					1.10	
	24/250	89.0	81.5	8.0	11	112.4	1.38					1.13	
			81.6		10							1.10	
20.0	8/250	89.4	81.3	6.0	9	107.3	1.32					1.02	
	16/250	89.4	82.1	8.5	9	106.7	1.30					1.01	
	24/250	88.9	81.5	7.5	10	108.8	1.33					1.05	
			81.6		9							1.03	

NOTES FOR TABLE 20

1. 1-1/16" diameter threaded end notched tensile specimens from 1.30" or 1.26" thick plate.
2. 0.50" diameter tapered seat notched tensile specimens from 1.163" to 1.004" thick plate. The NTS/YS ratio obtained using 0.50" diameter notched tensile specimens converted to NTS/YS ratio for 1-1/16" diameter specimens using correlation developed at Alcoa Laboratories.
3. Initial plate thickness - 1.30".
4. Initial plate thickness - 1.26".

0.357" diameter tapered seat tensile specimens tested for properties.

Plate solution heat treated 2 hrs at 960°F, cold water quenched, aged 6 hrs at 220°F 4 days after quenching, cold rolled indicated amount, and second-step aged as indicated.

Yield strength = 0.2% offset.

MT No. 090573-D

<u>Composition</u>						
<u>Si</u>	<u>Fe</u>	<u>Cu</u>	<u>Mn</u>	<u>Mg</u>	<u>Cr</u>	<u>Zn</u> <u>Ti</u>
0.07	0.05	1.70	0.02	2.40	0.18	5.80 0.00

TABLE 21

FABRICATION OF 1.00" THICK 7475 PLATE FOR BALLISTIC EVALUATION BY FRANKFORD ARSENAL

Plate S. No.	10"x9"x20" Rolling Sections				Rolled Slab (Entry Ends Beveled)				Recrystal- lization			Rolling at 750°F Reduc- tion, %	Sol.Ht Hrs/°F	Aging Pract.
	Sections Fabricated	Thermal Treat- ment	Rolling		Thermal Treat- ment	Thick, in.	Temp, °F	Reduc- tion, %	Thick, in.	Treat- ment, Hrs/°F				
			Temp, °F	Reduc- tion, %										
422622-1	422622A,B,C	A	750	30	A	7.00	500	82	1.25	10/960	20	2/960	A	
422622-2	422622A,B,C	A	750	30	A	7.00	500	79	1.45	10/960	22	2/960	B	

Ingot Thermal Practice "A" - Heated 6 hrs at 860°F plus 20 hrs at 960°F.


Slab Thermal Practice "A" - Heated 2 hrs at 960°F, cooled to 775°F at 50°F/hr, soaked 2 hrs at 775°F, cooled to 500°F at 50°F/hr, and soaked at least 4 hrs at 500°F.

Aging Practice "A" - 1.00" thick plate aged 24 hrs at 250°F plus 4 hrs at 350°F 4 days after quenching.


Aging Practice "B" (FTMT) - 1.13" thick plate aged 6 hrs at 220°F 4 days after quenching, cold rolled 12%, and aged 8 hrs at 250°F.

Composition

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti
0.07	0.05	1.70	0.02	2.40	0.18	5.80	0.00




CROPPING OF 12"×38"×100" DC INGOTS



SECTIONING OF 12"×38"×80" CROPPED D.C. INGOTS TO OBTAIN 12
12"×9"×20" SECTIONS FROM EACH INGOT


Figure 1



10" × 9" × 20" ROLLING SECTIONS USED IN I.T.M.T. EVALUATION

Figure 2


1.00" - 1.15" THICK PLATE



TENSILE PROPERTIES

- LONG-TRANSVERSE T1
- 0.357" ϕ TAPERED SEAT TENSILE SPECIMEN
- NOTCHED TENSILE STRENGTH
- LONG-TRANSVERSE T2
- 0.500" ϕ TAPERED SEAT NOTCHED TENSILE SPECIMEN

1.25" THICK PLATE



TENSILE PROPERTIES


- LONGITUDINAL (L1, L2). LONG-TRANSVERSE (T1, T2)
- 0.357" ϕ TAPERED SEAT TENSILE SPECIMEN
- SHORT-TRANSVERSE (N1, N2) 0.125" ϕ TAPERED SEAT TENSILE SPECIMEN
- NOTCHED TENSILE STRENGTH
- LONGITUDINAL (L3, L4). LONG-TRANSVERSE (T3, T4)
- 1 1/16" ϕ THREADED END NOTCHED TENSILE SPECIMENS
- FRACTURE TOUGHNESS (K_{Ic})
- LONGITUDINAL (L5, L6). LONG-TRANSVERSE (T5, T6)
- 1.00" THICK COMPACT TENSION FRACTURE TOUGHNESS SPECIMEN

ALL SPECIMENS FROM 1/2 LOCATION

LOCATION AND TYPE OF SPECIMENS USED IN EVALUATING
PROPERTIES OF 1.00" TO 1.25" THICK 7475 AND Al-Zn-Mg
ALLOY PLATE

Figure 3

1.50" THICK PLATE



* TENSILE PROPERTIES

LONGITUDINAL (L1), LONG-TRANSVERSE (T1)
0.357" ϕ TAPERED SEAT TENSILE SPECIMEN
SHORT-TRANSVERSE (N1) 0.125" ϕ TAPERED
SEAT TENSILE SPECIMEN


NOTCHED TENSILE STRENGTH

LONGITUDINAL (L2), LONG-TRANSVERSE (T2)
1 1/8" ϕ THREADED END NOTCHED TENSILE SPECIMEN
SHORT-TRANSVERSE (N2) 0.500" ϕ TAPERED
SEAT NOTCHED TENSILE SPECIMEN

FRACTURE TOUGHNESS (K_{Ic})

LONGITUDINAL (L3), LONG-TRANSVERSE (T3)
1.00" THICK COMPACT
TENSION FRACTURE TOUGHNESS SPECIMEN
SHORT-TRANSVERSE (N3) 0.50" THICK COMPACT
TENSION FRACTURE TOUGHNESS SPECIMEN

2.50" THICK PLATE



TENSILE PROPERTIES

LONGITUDINAL (L1, L2), LONG-TRANSVERSE (T1, T2)
0.357" ϕ TAPERED SEAT TENSILE SPECIMEN
SHORT-TRANSVERSE (N1, N2) 0.125" ϕ OR 0.250" ϕ TAPERED
SEAT TENSILE SPECIMEN

NOTCHED TENSILE STRENGTH

LONGITUDINAL (L3, L4), LONG-TRANSVERSE (T3, T4)
1 1/8" ϕ THREADED END NOTCHED TENSILE SPECIMEN
SHORT-TRANSVERSE (N3, N4) 0.500" ϕ TAPERED
SEAT NOTCHED TENSILE SPECIMEN


FRACTURE TOUGHNESS (K_{Ic})

LONGITUDINAL (L5, L6), LONG-TRANSVERSE (T5, T6)
1.00" THICK COMPACT TENSION FRACTURE TOUGHNESS SPECIMEN
SHORT-TRANSVERSE (N5, N6) 0.50" THICK COMPACT
TENSION FRACTURE TOUGHNESS SPECIMEN

ALL SPECIMENS FROM T/2 LOCATION

LOCATION AND TYPE OF SPECIMENS USED IN EVALUATING
PROPERTIES OF 1.50" AND 2.50" THICK 7475 AND Al-Zn-Mg
ALLOY PLATE

Figure 4



MAG: 100X

ETCH: KELLERS

1.25" THICK 7475-T6 PLATE S-427507


INGCT			SLAB			RECRYSTALLIZATION			PLATE					
THERMAL ¹¹		ROLLING	THICK	THERMAL ¹¹		THICK	ROLLING		SOLUTION ¹¹	GRAIN COUNT				
TREATMENT	TEMP	RGD		TREATMENT	TEMP		RGD	TREATMENT		AT 750°F	RGD	HEAT-TREAT	g/mm	
											X	Y	Z	XYZ
48hr/860°F 5hr/775°F	500°F	81%		NONE		190"	10hr/860°F	35%	3hr/900°F		13	8	52	5 408

(1) THERMAL TREATMENTS CARRIED OUT IN A SALT BATH

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _D ksi√in.
L	80.4	70.4	16.1	24	96.2	1.37	38.6
T	78.9	68.7	14.6	24	81.5	1.19	30.1
N	78.8	69.6	8.0	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK RECRYSTALLIZED PLUS
HOT ROLLED (AR + HR) 7475-T6 PLATE S-427507

Figure 5



MAG: 100X

ETCH: KELLERS

1.25" THICK 7475-T6 PLATE S-422622-A


INGOT			SLAB			RECRYSTALLIZATION			PLATE					
THERMAL ⁽¹⁾ TREATMENT	ROLLING		THICK	THERMAL ⁽¹⁾ TREATMENT	ROLLING		THICK	THERMAL ⁽¹⁾ TREATMENT	ROLLING AT 750°F RGD	SOLUTION ⁽¹⁾ HEAT-TREAT	GRAIN COUNT			
	TEMP	RGD			TEMP	RGD					g/mm		g/mm ³	
											X	Y	Z	XYZ
6hr/860°F 20hr/960°F	750°F	30%	7 0"	2hr/960°F 2hr/775°F 4hr/500°F	500°F	75%	1 75"	10hr/960°F	28%	2hr/960°F	21	14	63	18.522

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K ₀ ksi√in.
I	83.2	73.6	16.7	37	100.8	1.37	33.2
I	80.1	70.0	17.1	31	91.0	1.30	30.6
N	80.5	70.0	14.0	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK RECRYSTALLIZED PLUS
HOT ROLLED (AR + HR) 7475-T6 PLATE S-422622-A

Figure 6



MAG: 100X

ETCH: KELLERS

1.25" THICK 7475-T6 PLATE S-422622-B1


INGOT			SLAB			RECRYSTALLIZATION			PLATE					
THERMAL ⁽¹⁾ TREATMENT	ROLLING		THICK	THERMAL ⁽¹⁾ TREATMENT	ROLLING		THICK	THERMAL ⁽¹⁾ TREATMENT	ROLLING AT 750°F RGD	SOLUTION ⁽¹⁾ HEAT-TREAT	GRAIN COUNT			
	TEMP	RGD			TEMP	RGD					g/mm		g/mm ³	
											X	Y	Z	XYZ
6hr/860°F	750°F	30%	7 0"	2hr/960°F	500°F	75%	1 75"	10hr/960°F	28%	2hr/960°F	22	14	60	18 480
20hr/960°F				2hr/775°F										
				4hr/500°F										

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _D ksi√in.
L	83.8	73.4	16.4	21	98.9	1.35	42.6
T	82.4	72.0	13.6	27	98.2	1.36	32.4
N	79.9	67.5	13.0	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK RECRYSTALLIZED PLUS
HOT ROLLED (AR + HR) 7475-T6 PLATE S-422622 B1

Figure 7



MAG: 100X

ETCH: KELLERS

1.50" THICK 7475-T6 PLATE S-418967-50


INGOT				SLAB				RECRYSTALLIZATION				PLATE			
THERMAL ⁽¹⁾ TREATMENT	ROLLING			THERMAL ⁽¹⁾ TREATMENT	ROLLING			THERMAL ⁽¹⁾ TREATMENT	ROLLING AT 750°F		SOLUTION ⁽¹⁾ HEAT-TREAT	GRAIN COUNT			
	TEMP	RGD	THICK		TEMP	RGD	THICK		RGD			g/mm		g/mm ³	
												X	Y	Z	XYZ
6hr/860°F 20hr/960°F	750°F	14%	8.0"	2hr/960°F 2hr/775°F 4hr/500°F	500°F	75%	2.0"	8hr/960°F	25%		2 hr/960°F	24	11	62	16,368

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _G ksi√in.
L	82.1	70.6	17.1	28	97.1	1.37	29.9
T	80.5	69.0	15.0	25	84.7	1.23	29.2
N	79.3	66.3	12.0	N.D.	79.2	1.20	29.0

MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK RECRYSTALLIZED
AND HOT ROLLED (AR+HR) 7475-T6 PLATE S-418967-50

Figure 8



MAG: 100X

ETCH: KELLERS

2.50" THICK 7475-T6 PLATE S-422622-G1


INGOT			SLAB			RECRYSTALLIZATION			PLATE						
THERMAL TREATMENT	ROLLING		THICK	THERMAL TREATMENT	ROLLING		THICK	THERMAL TREATMENT	ROLLING AT 750 F RGD	SOLUTION HEAT-TREAT	GRAIN COUNT				
	TEMP	RGD			TEMP	RGD					g/mm			g/mm	
											X	Y	Z	XYZ	
6hr/860°F	500°F	65%	NONE					3.50"	10hr/960°F	28%	2hr/960°F	14	8	42	4704
20hr/960°F															
2hr/775°F															
4hr/500°F															

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _Q ksi√in.
L	79.2	68.6	20.7	27	92.0	1.34	N.D.
T	78.6	67.4	14.3	28	84.8	1.26	N.D.
N	77.7	65.2	13.0	N.D.	92.7	1.42	N.D.

MICROSTRUCTURE AND PROPERTIES OF 2.50" THICK RECRYSTALLIZED PLUS
HOT ROLLED (AR + HR) 7475-T6 PLATE S-422622-G1

Figure 9



MAG: 100X

ETCH: KELLERS

1.25" THICK 7475-T6 PLATE S-427506

INGOT			SLAB			RECRYSTALLIZATION			PLATE						
THERMAL ¹⁾ TREATMENT	ROLLING		THICK	THERMAL ¹⁾ TREATMENT	ROLLING		THICK	THERMAL ¹⁾ TREATMENT	ROLLING AT 750°F RGD	SOLUTION ¹⁾ HEAT-TREAT	GRAIN COUNT				
	TEMP	RGD			TEMP	RGD					g/mm			g/mm ² XYZ	
											X	Y	Z		
48hr/860°F	500°F	88%	—	NONE	—	1.25"	48hr/860°F	NONE	3hr/900°F	18	12	61	13.176		
5hr/775°F															
4hr/500°F															


(1) THERMAL TREATMENTS CARRIED OUT IN A SALT BATH

PROPERTIES

DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K ₀ ksi√in.
L	78.5	68.6	19.3	40.5	95.0	1.38	33.6
T	78.7	67.8	17.1	32.0	84.0	1.24	29.3
N	80.9	71.1	14.0	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK RECRYSTALLIZED (AR) 7475-T6 PLATE S-427506

Figure 10



MAG: 100X

1.25" THICK 7475-T6 PLATE S-421675-E61

ETCH: KELLERS


INGOT			SLAB			RECRYSTALLIZATION			PLATE								
THERMAL ¹		ROLLING		THICK	THERMAL ¹		ROLLING		THICK	THERMAL ¹		AT 750 F	SOLUTION ¹	GRAIN COUNT			
TREATMENT	TEMP	RGD	TREATMENT		TEMP	RGD	TREATMENT	RGD		TREATMENT	RGD			HEAT-TREAT	g mm		
														X	Y	Z	XYZ
6hr/860° F	750° F	50%	5.0"	2hr/960° F	500° F	75%	1.25"	10hr/960° F	NONE	2hr/960° F	30	23	48	33	120		
20hr/960° F				2hr/775° F													
				4hr/650° F													

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	KQ ksi√in.
L	75.2	64.8	19.6	40	95.7	1.49	40.2
T	77.1	66.3	17.1	30	84.7	1.32	32.2
N	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK RECRYSTALLIZED (AR) 7475-T6 PLATE S-421675-E61

Figure 11



MAG: 100X

ETCH: KELLERS

1.50" THICK 7475-T6 PLATE S-418967-40


INGOT			SLAB			RECRYSTALLIZATION			PLATE								
THERMAL ¹		ROLLING		THICK	THERMAL ¹		ROLLING		THICK	THERMAL ¹		AT 750 F	SOLUTION ¹	GRAIN COUNT			
TREATMENT	TEMP	RGD	TREATMENT		TEMP	RGD	TREATMENT	RGD		HEAT-TREAT	X			Y	Z	XYZ	
6hr/860 F	750 F	35%	6.0"	2hr/960°F	500°F	75%	1.50"	18hr/960°F	NONE	2hr/960 F	22	20	54	23 760			
20hr/960 F				2hr/775°F													
				4hr/500°F													

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K ₀ ksi√in.
L	79.3	67.7	17.9	32	90.1	1.33	32.4
T	80.2	68.5	15.7	22	82.1	1.20	27.5
N	79.3	67.4	8.0	N.D.	85.0	1.27	23.6

MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK RECRYSTALLIZED (AR) 7475-T6 PLATE S-418967-40

Figure 12



MAG: 100X

2.50" THICK 7475-T6 PLATE S-421675-F3

ETCH: KELLERS


INGOT			SLAB			RECRYSTALLIZATION			PLATE					
THERMAL ¹ TREATMENT	ROLLING		THICK	THERMAL ¹ TREATMENT	ROLLING		THICK	THERMAL ¹ TREATMENT	ROLLING AT 750 F RGD	SOLUTION ¹ HEAT-TREAT	GRAIN COUNT			
	TEMP	RGD			TEMP	RGD					g/mm		g/inm ²	
											X	Y	Z	XYZ
6hr/860 F 20hr/960 F 2hr/775 F 4hr/650 F	600 F	50%	5.0"	10hr/960 F	600 F	50%	2.50"	10hr/960 F	NONE	2hr/960 F	9	5	24	1080
2hr/960 F														
2hr/775 F														
4hr/650 F														

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	KQ ksi√in.
L	75.9	65.2	17.1	28	84.3	129	N.D.
T	75.4	64.8	16.4	24	79.0	122	N.D.
N	76.2	63.3	12.0	N.D.	91.2	144	N.D.

MICROSTRUCTURE AND PROPERTIES OF 2.50" THICK RECRYSTALLIZED
(AR) 7475-T6 PLATE S-421675-F3

Figure 13



MAG: 100X


ETCH: KELLERS

1.25" THICK HOT ROLLED (HR) 7475-T6 PLATE S-422622-C2

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	KQ ksi√in.
L	83.7	74.0	13.2	17	99.3	1.34	49.9
T	80.4	70.7	10.7	12	92.8	1.31	43.1
N	76.1	65.9	9.0	N.D.	N.D.	N.D.	N.D.

MICROSTRUCTURE AND PROPERTIES OF 1.25" THICK HOT ROLLED
(HR) 7475-T6 PLATE S-422622-C2

Figure 14



MAG:100X


ETCH:KELLERS

1.50" THICK HOT ROLLED (HR) 7475-T6 PLATE S-418967-30

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _Q ksi√in.
L	83.8	73.0	15.0	19	99.8	1.37	40.9
T	81.3	70.3	15.7	21	90.0	1.28	32.6
N	81.4	67.1	10.0	N.D.	85.3	1.28	31.0

MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK HOT ROLLED
(HR) 7475-T6 PLATE S-418967-30

Figure 15



MAG. 100X

ETCH: KELLERS


2.50" THICK HOT ROLLED (HR) 7475-T6 PLATE S-422622-C1

PROPERTIES

DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _Q ksi√in.
L	83.9	74.4	11.0	12	98.6	1.33	N.D.
T	76.5	67.8	5.7	8	94.0	1.39	N.D.
N	73.0	60.2	10.0	N.D.	94.2	1.56	N.D.

MICROSTRUCTURE AND PROPERTIES OF 2.50" THICK HOT ROLLED
(HR) 7475-T6 PLATE S-422622-C1

Figure 16




RECRYSTALLIZED
PLUS HOT WORKED RECRYSTALLIZED



INGOT BROKEN DOWN AT 750°F AND WARM ROLLED AT 570°-600°F
INGOT BROKEN DOWN AT 750°F AND WARM ROLLED AT 500°F
INGOT WARM ROLLED AT 500°F

EFFECT OF WARM ROLLING REDUCTIONS ON GRAIN DIMENSIONS OF
1.25" - 1.50" THICK RECRYSTALLIZED AND RECRYSTALLIZED PLUS
HOT WORKED 7475-T6 PLATE FABRICATED USING ITMT PRACTICES

Figure 17



RECRYSTALLIZED &

HOT ROLLED

RECRYSTALLIZED

○

□

INGOT BROKEN DOWN AT 750°F AND WARM ROLLED AT 575°-600°F

○

□


INGOT WARM ROLLED AT 575°-600° F

●

INGOT WARM ROLLED AT 500°F


EFFECT OF WARM ROLLING REDUCTIONS ON GRAIN DIMENSIONS OF
2.50" THICK RECRYSTALLIZED AND RECRYSTALLIZED PLUS HOT
WORKED 7475-T6 PLATE FABRICATED USING ITMT PRACTICES

Figure 18




LONGITUDINAL PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE
AS A FUNCTION OF YIELD STRENGTH

Figure 19




LONG TRANSVERSE PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF YIELD STRENGTH




SHORT-TRANSVERSE PROPERTIES OF 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF YIELD STRENGTH

Figure 21




LONGITUDINAL PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF GRAIN DIMENSION IN THE SHORT-TRANSVERSE DIRECTION

Figure 22




LONG TRANSVERSE PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE
AS A FUNCTION OF THE GRAIN DIMENSION IN THE SHORT TRANSVERSE DIRECTION

Figure 23




SHORT-TRANSVERSE PROPERTIES OF 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF THE GRAIN DIMENSION IN THE SHORT-TRANSVERSE DIRECTION

Figure 24




LONGITUDINAL PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF THE GRAIN DIMENSION IN THE LONGITUDINAL DIRECTION

Figure 25




LONG-TRANSVERSE PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF THE GRAIN DIMENSION IN THE LONGITUDINAL DIRECTION

Figure 26




SHORT-TRANSVERSE PROPERTIES OF 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF THE GRAIN DIMENSION IN THE LONGITUDINAL DIRECTION

Figure 27




LONGITUDINAL PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE
AS A FUNCTION OF THE ASPECT RATIO OF THE GRAINS

Figure 28




LONG-TRANSVERSE PROPERTIES OF 1.25" AND 2.50" THICK 7475-T6 PLATE AS A FUNCTION OF THE ASPECT RATIO OF THE GRAINS

Figure 29



SHORT-TRANSVERSE PROPERTIES OF 2.50" THICK 7475-T6 PLATE AS
 A FUNCTION OF THE ASPECT RATIO OF THE GRAINS


Figure 30



- RECRYSTALLIZED PLUS HOT ROLLED (AR + HR)
- ◐ RECRYSTALLIZED (AR)
- HOT ROLLED (HR) (UNRECRYSTALLIZED)


PROPERTIES OF 1.50" THICK 7475-T6 PLATE
AS A FUNCTION OF YIELD STRENGTH

Figure 31




EFFECT OF AMOUNT OF COLD ROLLING ON THE LONG-TRANSVERSE PROPERTIES OF 1.00" TO 1.30" THICK 7475-TX PLATE FABRICATED USING FTMT PRACTICES

Figure 32



NTS/YS RATIO - YIELD STRENGTH RELATIONSHIP FOR 1.00" TO 1.30" THICK
7475 PLATE PROCESSED USING FTMT PRACTICES

Figure 33



MAG: 100X

ETCH: KELLERS

1.00" THICK 7475-T7X PLATE S-422622-1

INGOT				SLAB				RECRYSTALLIZATION				PLATE ²			
THERMAL ¹		ROLLING		THERMAL ¹		ROLLING		THERMAL ¹		ROLLING		SOLUTION ¹		GRAIN COUNT	
TREATMENT	TEMP	RGD	THICK	TREATMENT	TEMP	RGD	THICK	TREATMENT	RGD	AT 750°F	HEAT-TREAT	HEAT-TREAT	HEAT-TREAT	g/mm ²	g/mm ²
														X	Y
														Z	XYZ
6hr/860°F	750°F	30%	7 0"	2hr/960°F	500 F	82%	1 25"	10hr/960°F	20%	2hr/960°F	22	12	50	13	200
20hr/960°F				2hr/775°F											
				4hr/500°F											


(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

(2) PLATES ARTIFICIALLY AGED 24hr/25° + 4hr/350°F

PROPERTIES			
DIR	T.S. ksi	Y.S. ksi	EL %
T	75.4	63.7	15.0

MICROSTRUCTURE AND PROPERTIES OF 1.00" THICK RECRYSTALLIZED PLUS
HOT ROLLED (AR + HR) 7475-T7X PLATE FABRICATED FOR
BALLISTIC EVALUATION S-422622-1

Figure 34



MAG: 100X

ETCH: KELLERS

1.00" THICK 7475-T6X PLATE S-422622-2

INGOT				SLAB				RECRYSTALLIZATION				PLATE			
THERMAL ⁽¹⁾		ROLLING		THERMAL ⁽¹⁾		ROLLING		THERMAL ⁽¹⁾		ROLLING		SOLUTION ⁽¹⁾		GRAIN COUNT	
TREATMENT	TEMP	RGD	THICK	TREATMENT	TEMP	RGD	THICK	TREATMENT	TEMP	RGD	THICK	HEAT-TREAT	TEMP	X	Y
6hr/860°F	750°F	30%	7.0"	2hr/960°F	500°F	79%	1.45"	10hr/960°F	22%			2hr/960°F		24	16
20hr/960°F				2hr/775°F										68	26112
				4hr/500°F											

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

(2) PLATE SOLUTION HEAT-TREATED AND QUENCHED AT 113°. ARTIFICIALLY

AGED 6hr/220°F. COLD ROLLED 12% AND AGED 8hr/250°F

DIR	T.S. ksi	Y.S. ksi	El %
T	86.8	76.8	12.0

**MICROSTRUCTURE AND PROPERTIES OF 1.00" THICK RECRYSTALLIZED
PLUS HOT ROLLED (AR+HR) 7475-FTMT PLATE
FABRICATED FOR BALLISTIC EVALUATION S-422622-2**

Figure 35

APPENDIX ARecrystallization Procedure

The use of a 10-hour at 960°F recrystallization treatment for the ITMT processed 7475 and Al-Zn-Mg alloy plate fabricated at Alcoa Laboratories raised questions as to the effect of time at the recrystallization temperature, the temperature at which recrystallization is achieved and the time required to reach the recrystallization temperature on the grain size of the recrystallized plate. Answers to these questions were not available and a limited investigation was carried out at Alcoa Laboratories to obtain the desired answers. In this work, 1" x 1" x full thickness samples were sawed from plate samples after the warm rolling operation and subjected to various thermal treatment.


Samples of warm rolled plate fabricated using rolling sections 421675A, C, D, E, and F and 422014A, C, D, E, and F were heated 4 hours at 860°F and 10 hours at 960°F using a circulating air furnace. Microscopic examination of the samples showed that for each alloy and fabrication practice the recrystallization procedure of 10 hours at 960°F produced grain lengths and thicknesses that were the same or less than the grain dimensions produced by the heating procedure of 4 hours at 860°F. Further work using samples of warm rolled plate fabricated using rolling sections 421675G, H, J, L, and I and 422014G, H, J, L, and I in which the samples were heated to 960°F in 1 minute (salt bath), 30 minutes (circulating air furnace) and 3 hours (programmed heatup in a circulating air furnace)

showed that increasing the time required to reach the recrystallization temperature of 960°F did not increase the grain length or grain thickness of the recrystallized grains in the plate samples.

Samples of 1.25" thick 7475 plate, S-421675E6, warm rolled at 500°F were recrystallized by soaking 1, 4.5, 10, and 20 hours at 860°F or 960°F. Microscopic examination of the samples showed no significant difference in the grain length or thickness that could be attributed to either the soak time at the recrystallization temperature and/or the recrystallization temperatures of 860 or 960° F.


Thus, it was shown that the use of a 10-hour at 960°F recrystallization treatment and the use of circulating air furnaces to carry out the recrystallization treatments in the ITMT work carried out at the Alcoa Laboratories would not be expected to have a detrimental effect on the size of the grains obtained in the recrystallized 7475 and Al-Zn-Mg alloy plate.

APPENDIX B




FABRICATION DETAILS FOR INGOT SECTIONS 421675A AND 422014A

Figure B1




FABRICATION DETAILS FOR INGOT SECTIONS 421675-B AND 422014-B

Figure B2 -




FABRICATION DETAILS FOR INGOT SECTIONS 421675-C AND 422014-C

Figure B3




FABRICATION DETAILS FOR INGOT SECTIONS 421675-D AND 422014-D

Figure B4




FABRICATION DETAILS FOR INGOT SECTIONS 421675-E AND 422014-E

Figure B5




FABRICATION DETAILS FOR INGOT SECTIONS 421675-F AND 422014-F

Figure B6




FABRICATION DETAILS FOR INGOT SECTIONS 421675-G AND 422014-G

Figure B7




FABRICATION DETAILS FOR INGOT SECTIONS 421675H AND 422014-H

Figure B8




FABRICATION DETAILS FOR INGOT SECTIONS 421675-I AND 422014-I

Figure B9




FABRICATION DETAILS FOR INGOT SECTIONS 421675-J AND 422014-J

Figure B10




FABRICATION DETAILS FOR INGOT SECTIONS 421675-K AND 422014-K

Figure B11




FABRICATION DETAILS FOR INGOT SECTIONS 421675-L AND 422014-L

Figure B12




FABRICATION DETAILS FOR INGOT SECTIONS 422622-A AND -B

Figure B13




FABRICATION DETAILS FOR INGOT SECTION 422622-C

Figure B14



FABRICATION DETAILS FOR INGOT SECTIONS 422622-E AND -G

Figure B15



PROCEDURES USED TO FABRICATE 1.50" THICK 7475-T6 PLATE

Figure B16

1.75" THICK 747S PLATE
S-422622A RECONSTRUCTED & HOT ROLLED
S-422622C2 ALCOA PRACTICE

SOLUTION HEAT-TREATED 2 HRS AT 960°F & COLD WATER QUENCHED

AGED 6 HRS AT 220°F 4 DAYS AFTER QUENCHING

COLD ROLLED

S-422622A 1.299 TO 1.163 (10.5%)
S-422622C2 1.260 TO 1.141 (9.5%)

S-422622A 1.297 TO 1.084 (16.4%)
S-422622C2 1.262 TO 1.076 (14.7%)

S-422622A 1.298 TO 1.004 (22.6%)
S-422622C2 1.256 TO 1.004 (20.0%)

SECOND STEP AGED AT 250°F

8 HOURS
422622A-10
422622C2-10

16 HOURS
422622A-11
422622C2-11

24 HOURS
422622A-12
422622C2-12

8 HOURS
422622A-20
422622C2-20

16 HOURS
422622A-21
422622C2-21

24 HOURS
422622A-22
422622C2-22


8 HOURS
422622A-30
422622C2-30

16 HOURS
422622A-31
422622C2-31

24 HOURS
422622A-32
422622C2-32

PROCEDURES USED TO EVALUATE FTMT PRACTICES ON 1.25" THICK 747S PLATE


Figure B17



PROCEDURES USED TO FABRICATE 1.00" THICK PLATE FOR BALLISTIC EVALUATION

Figure B18

BEST AVAILABLE COPY



NOTE: Short-transverse specimens from plate thinner than 5-1/2 in. have shortened reduced sections. Specimens from plate thinner than 1-1/8 in. have small flats on threads.


Notch-Tip Radius
= 0.0005 in.

Sharply Notched Round Tensile Specimens
(1-1/16-in. dia.).

Figure C1


BEST AVAILABLE COPY

Notch - tip radius ≥ 0.0005 ", $K_t \geq 16$




Sharply Notched 1/2-in. Diameter Notch-Tensile Specimen (Tapered Seat).

Figure C2



NOTCH ROOT
RADIUS .010" MAX.



NOTCH

ENLARGED VIEW

PROPORTIONS

$B = \text{THICKNESS}$

$A \approx 1.1B$

$W \approx 2B ; W_1 \approx 2.5B$

$S \approx 0.1B$

$F \approx 2E \approx 1.10B$

$H \approx 1.2B$

$D \approx 0.5B$

COMPACT TENSION FRACTURE TOUGHNESS SPECIMEN

Figure C3

TABLE D1

RESULTS OF MULTIPLE LINEAR REGRESSION ANALYSES OF LONGITUDINAL DATA FOR 7475-T6 PLATE

Coefficients in Multiple Linear Regression Equation										
Type Data	Y.S., ksi	T, in.	Fe, wt. %	Grain Dimensions,					Intercept	Multiple Correlation
				Structure ¹	$\frac{1}{T, \text{mm}}$		$\frac{1}{L, \text{mm}}$			
					Longitudinal Elongation, %					

NOTES FOR TABLE D1

Note 1. To obtain a quantitative representation of a qualitative variable in regression analysis: when three structures available, unrecrystallized represented by 0:0, recrystallized represented by 1:0, and recrystallized plus hot worked represented by 0:1. When two structures available, recrystallized represented by 1, recrystallized plus hot worked represented by 0.

Type Data: 1 - regression determined using data for unrecrystallized, recrystallized, and recrystallized plus hot worked plate; 2 - regression determined using data for recrystallized and recrystallized plus hot worked plate.

T = thickness, L = length.

N.U. = not used.

APPENDIX E

Analysis of Smooth Versus Notch-Tensile Data

Supplementary smooth and notch-tensile tests were conducted on samples of 1.50" thick 7475-T6 plate having a recrystallized, a recrystallized plus hot rolled, and an unrecrystallized structure to help explain the relation between the ductility and K_Q values for the recrystallized, recrystallized plus hot rolled, and unrecrystallized materials. The tests included one tensile and one notched specimen from each sample of plate. The smooth specimens were 0.357" dia. with no tapered section, while the notched specimens were 0.505" gross section diameter and 0.353" net section diameter. The results of tests are given in Table E1.

Table E2 shows the ratio of the notch-tensile stress to the smooth tensile stress at fracture using both engineering stress (original cross-sectional area) and true stress (final cross-sectional area). This ratio is called the notch sensitivity index and is a measure of a material's resistance to triaxial stress fields induced by notches. In general, for a fixed specimen size the lower this ratio, the more sensitive the material is to notches and the lower will be the fracture toughness. As shown in Table E2, if engineering stress is used, the recrystallized material is most sensitive to notches while the recrystallized plus hot rolled material is least. If true stress is used, the recrystallized material is still most sensitive to notches, but the unrecrystallized material is least. True stress is probably a better comparison since it takes account of area changes beyond instability (necking). Based on these true stress NTS/TS ratios, one could infer

that the fracture toughness, K_{IC} , of the recrystallized material would be lower than that of either the recrystallized plus hot rolled or unrecrystallized materials and that the unrecrystallized material should give the highest K_{IC} values of the three.

A word of caution is in order here. The fracture toughness, K_{IC} , is supposed to be a measure of a material's resistance to crack propagation. A means of insuring this is to fatigue precrack the specimen prior to testing to insure a crack-like defect for measuring propagation with no initiation phase. The notch-tensile test, on the other hand, is not fatigue precracked, and hence measures both initiation and propagation of a crack. What is being implied in the prediction of K_{IC} trends from NTS/TS ratio trends is that the distinction between initiation and propagation is relatively unimportant in this particular instance and what really matters is how the material reacts to any triaxial stress field at a notch, regardless of whether the notch is sharp or blunt.

Additional smooth and notch-tensile tests were made on samples of 1.50" thick 7475-T6 plate which were quenched as 0.600" dia. blanks. The results of the tensile tests are given in Table E3. The tensile and yield strengths and the load at fracture for the notched specimens were higher for the specimens from the material quenched as 0.600" dia. blanks than for the specimens from the material quenched as 1.50" thick plate.

The notched tensile stress/tensile stress ratio (notch sensitivity index) was calculated for the rapidly quenched material using true stress and is given in Table E4 along with the results of

the calculations made for the material quenched as 1.50-in. thick plate. The test data show that even though increasing the quench rate has increased the yield, ultimate, and notch-tensile strengths, the notch sensitivities of the materials have remained unchanged. The unrecrystallized material is still the least notch sensitive and should give higher toughness than either the recrystallized or the recrystallized plus hot rolled material.

In reaching the conclusions discussed here, it is assumed that the constraint conditions at the notch in the notched round bar tests for all materials are roughly the same; that is, the differences in yield strengths of the materials is assumed small and hence the constraint conditions at the notch are similar in all cases. With this assumption, one is then able to say that for the same constraint, one material behaves differently than another under triaxial stress conditions.

TABLE E1

RESULTS OF TENSILE AND NOTCHED TENSILE TESTS ON 1.50" THICK 7475-T6 PLATE,
S-418967-30, 40, 50 - MATERIAL QUENCHED AS 1.50" THICK PLATE

Structure	Y.S., ksi	Elongation	Load at	Change in Dia. at Fracture, 1 %	Area at Fracture, in. ²	True Stress at Fracture, ksi
		at Fracture, %	Fracture, lb			
<u>Smooth Specimens</u>						
Unrecrystallized	73.0	17.1 ²	7840	13.08	0.0756	103.70
Recrystallized	67.7	19.3 ²	7720	13.84	0.0743	103.90
Recrystallized plus hot rolled	70.6	20.0 ²	7600	16.30	0.0701	108.42
<u>Notched Specimens</u>						
Unrecrystallized	--	6.9 ³	9990	3.2	0.0917	108.94
Recrystallized	--	8.2 ³	9180	1.9	0.0942	97.45
Recrystallized plus hot rolled	--	6.4 ³	9700	1.9	0.0941	103.08

Notes: 1. Average of three diameter measurements taken from fractured specimen used to calculate area.
2. Gauge length = 1.4 in.
3. Gauge length = notch mouth at specimen surface - 0.854 in.

TABLE E2

NOTCHED TENSILE/TENSILE STRENGTH AND K_Q RESULTS,
1.50" THICK 7475-T6 PLATE, S-418967-30, 40,50 -
MATERIAL QUENCHED AS 1.50" THICK PLATE

Structure	Notched Tensile Strength/Tensile Strength		K_Q ksi/in.
	Engineering Stress	True Stress ¹	
Unrecrystallized	1.303	1.050 (100%)	40.9 ²
Recrystallized	1.243	0.938 (89.3%)	27.8 ³
Recrystallized plus hot rolled	1.305	0.951 (90.6%)	26.8 ³

- Notes: 1. Based on final area only. No correction for necking has been applied due to difficulty in measuring large radii of necked regions.
2. Based on 5% secant line on load displacement curve.
3. Based on initial stepwise departure from a smooth line.

TABLE F3

RESULTS OF TENSILE AND NOTCHED TENSILE TESTS ON 1.50" THICK 7475-T6 PLATE -
S-418967-30, 40, 50 - MATERIAL QUENCHED AS 0.600" Ø BLANKS

Structure	Yield Strength, ksi	Ultimate Strength, ksi	Load at Failure, lb	Reduction of area, %	Total Elongation, %
<u>Smooth Specimens</u>					
Unrecrystallized	75.0	84.2	8300	23	17.1
Recrystallized	70.1	79.8	7070	38	20.7
Recrystallized plus hot rolled	75.7	84.7	7480	36	19.3
<u>Notched Specimens</u>					
Unrecrystallized	--	110.8	10850	--	--
Recrystallized	--	108.3	10600	--	--
Recrystallized plus hot rolled	--	111.1	10870	--	--

APPENDIX E

TABLE E4

NOTCHED TENSILE/TENSILE STRENGTH RATIO BASED ON TRUE STRESSES
1.50" THICK 7475-T6 PLATE - S-418967-30, 40, 50

Structure	Notched Tensile Strength/Tensile Strength	
	Material Quenched as 1.50" Thick Plate	Material Quenched as 0.6"Ø Blanks
Unrecrystallized	1.050	1.033
Recrystallized	0.938	0.957
Recrystallized plus hot rolled	0.951	0.947

APPENDIX F

MICROSTRUCTURE VS. DUCTILITY AND TOUGHNESS

INTRODUCTION

The investigation reported in the main body of this report indicated that 7475 plate thermomechanically processed to produce recrystallized grains comparable in size to those reported by DiRusso et al and Waldman et al developed the anticipated high ductility (tensile reduction in area) relative to that of unrecrystallized 7475 plate. Toughness, however, measured using either compact tension fracture toughness specimens or circumferentially notched tension specimens was lower than that of the unrecrystallized plate. Examination of undeformed samples and of fracture specimens of the plates that were produced in the initial phases were difficult to interpret because the different thermomechanical histories produced differences in second phase particle morphologies along with differences in grain structure so that the relative effects of particles and of grain structure could not be separated. Consequently, additional plate samples from a new 7475 ingot were fabricated in Phase IV using identical procedures with the exception of rolling practices. Three structure variants were produced: (1) unrecrystallized, (2) recrystallized to a fine, relatively equiaxed grain structure, (3) a structure which was recrystallized, then hot rolled to elongate the recrystallized grains. Test results reported in the body of this report indicated that the toughness of these plates

were generally lower than the toughness of the 7475 plates produced during the initial phases. This difference was anticipated because of the higher impurity content of the ingot fabricated for the microstructural studies (Phase IV). The relative toughness and ductility differences between these unrecrystallized, recrystallized, and recrystallized plus hot worked structures were comparable, however, to the differences originally observed.

The object of this work was to establish in greater detail the nature of the microstructural differences and to relate them more closely with respect to deformation and fracture mechanisms to the observed differences in fracture toughness and ductility. Transmission electron microscopy (TEM), scanning electron microscopy (SEM), optical microscop, x-ray, and electron microprobe techniques were used.

EXPERIMENTAL

All the samples used for microstructural studies were the ones tested in the longitudinal direction. Samples for slip line studies were 0.065" thick, 3/8" wide and 2" long (gauge length). They were mechanically polished and then electropolished before subjecting them to deformation to fracture. Thin foils for TEM were electropolished using a solution consisting of 25 vol. % nitric acid and 75 vol. % methanol. A Philips EM301G microscope equipped with eucentric goniometer stage was used for the examination. The operating voltage of the microscope was 100 KV. Fractographs were prepared representing the fracture locations at the initial region of unstable crack propagation, and also in the vicinity of the stretched zone. In order to show the relation between second phase particles and the grains at fairly high magnification in the SEM, an etchant (10% bromine in methanol) was used which was known to

put the particles in relief without altering their appearance.

RESULTS

Undeformed Structure

The distributions of coarse constituent particles and dispersoid particles (E phase) are shown in the 500X and 2000X scanning electron micrographs in Fig. Fla-lc. Because of low Fe and Si contents, the volume fraction of large constituent particles (up to $\sim 10\mu\text{m}$) was low in all three structures. The largest insoluble constituents (a few microns to $\sim 10\mu\text{m}$) were identified as Al-Fe-Cu particles by energy dispersive x-ray (Kevex) and also by Guinier x-ray diffraction analyses. There were also some M (η) and very few S(CuMgAl_2) phase particles present in the alloy. The smallest particles shown in the figures are dispersoids (E phase particles).

In the unrecrystallized sample, the constituent particles were not preferentially located at the grain boundaries (Fig. Fla). However, in the recrystallized sample constituent particles were preferentially located along grain boundaries (Fig. Flb). Constituent particles also tended to lie along the elongated grain boundaries in the sample which was recrystallized and subsequently hot rolled (Fig. Flc). Three-dimensional light micrographs and the mechanical properties of these samples are shown in Figure F2a-F2c.

A typical electron microstructure representing the unrecrystallized material is shown in Fig. F3a and F3b. The dispersoids are the E phase described as $\text{Al}_{12}\text{Mg}_2\text{Cr}$ by Hunter and McMillan⁽¹⁾ and $\text{Al}_{18}\text{Cr}_3\text{Mg}_2$ by others⁽²⁾. Since all thermal treatments were the same for the three samples, there was no appreciable variation between samples in the size and distribution of the E phase particles. Different rolling temperatures, however,

gave rise to different substructures among the samples: cell structures in the unrecrystallized sample (Fig. F3a and F3b), relatively dislocation-free recrystallized grains in the recrystallized sample (Fig. F4a and F4b) and polygonized cells in the recrystallized plus hot rolled sample (Fig. F5). Even though there was no appreciable fluctuation in the distribution of Cr according to electron microprobe analysis (on a light microscope scale) the distribution of E phase was inhomogeneous (on an electron microscope scale).

Deformed Structure

In order to understand the mechanical properties in a precipitation hardened alloy, it is necessary to examine the interaction between the hardening particles and moving dislocations. If the particles are coherent, the moving dislocations can either shear them or by-pass them depending on the size, distribution and also volume fraction of the particles. The advantage of changing the deformation mechanism from a cutting to a by-pass mechanism (better ductility) was shown by Lütjering and Hornbogen⁽³⁾ and Lütjering and Weissmann⁽⁴⁾.

In this study the microstructural observations were made in a uniformly deformed region of each of the structures generated by the different thermomechanical histories. As will be discussed later, the mode of fracture seemed to be very important in controlling the toughness of the alloy. Therefore, the interaction between dislocations and precipitates along grain boundaries was also examined in addition to the interaction between dislocations and matrix precipitates.

Typical transmission electron micrographs showing the unrecrystallized sample after deformation are shown in Fig. F6a and F6b. The

distribution of dislocations was relatively homogeneous and there was no preferential deformation along the grain boundaries. Also, in most regions dislocation bands piled against the grain boundary were not observed (Fig. F6a). The moving dislocations by-passed the large constituent particles (intermetallic phase) and concentration of slip was observed. Due to the deformation, some of the rod-shaped particles thought to be $\text{Al}_7\text{Cu}_2\text{Fe}$ were fractured (Fig. F6b). However, there was no evidence of shearing of η' particles by the moving dislocations.

In contrast to the unrecrystallized sample, the recrystallized sample showed a quite different deformed microstructure (Fig. F7a and F7b). As shown in Fig. F7b, the grain boundary was much more heavily deformed compared to the grain-interior. Grain boundary dislocations (GBD) were proposed by Gleiter and his co-workers^(5,6) and Price and Hirth⁽⁷⁾. According to the former^(5,6) grain boundaries function as sources of dislocations, and two generation mechanisms are operative. In mobile grain boundaries GBD's move along the boundary. Also GBD's showed interactions similar to those of lattice dislocations such as networks, pile ups, etc. Dislocation bands, presumably generated by these grain boundary dislocations in the recrystallized material, are apparent in Fig. F7a and F7b.

In the recrystallized and hot rolled sample strong interaction between dislocation bands and grain boundaries was also observed (Fig. F8a and F8b). As in the recrystallized sample, heavier deformation resulted along the high angle grain boundaries.

Slip Line Study

When the unrecrystallized sample was deformed and the originally polished surface was examined in a light microscope, slip lines more or less uniformly distributed throughout the grains were observed along with a slight grain boundary sliding along high angle grain boundaries (Fig. F9a). Fracture, as shown in Fig. F9b and F9c usually followed slip bands and was predominantly transgranular.

In contrast to the unrecrystallized sample, the recrystallized sample showed much more grain boundary sliding and the fracture path usually followed grain boundaries rather than slip bands (Fig. F10a,b,c). In the recrystallized plus hot rolled sample, the slip line structure showed that cracking occurred along grain boundaries as well as at slip bands (Fig. F11a-F11c).

Fractography

To further determine differences in fracture mechanisms of the fracture toughness specimens, the fractured surfaces were examined in the scanning electron microscope. Observed fracture modes were consistent with the results from the slip line studies, and were closely related to the respective fracture toughness values determined in this investigation. The higher the proportion of intergranular fracture, the lower was the fracture toughness (Figs. F12, F13 and F14). The unrecrystallized sample had the highest toughness and fractured almost entirely by a transgranular mode (Figs. F9 and F12). The fracture surface exhibited large and small dimples (Fig. F12). The spacing of the small dimples was consistent with and apparently controlled by the average interparticle distance of the dispersoids (E phase). The recrystallized sample,

which showed the lowest toughness, had predominantly intergranular fracture and the fracture surface was almost free of small dimples (Fig. F13). On the other hand, the recrystallized plus hot rolled sample showed a transgranular-intergranular mixed mode fracture (Fig. F13) and generally had an intermediate level of toughness.

When fractures of the notched tensile specimens were compared to those of the corresponding fracture toughness specimens, the same mode of fracture was observed (compare Figs. F12, F13, and F14 with Figs. F15, F16, and F17).

According to other investigators^(8,9) other fracture features such as stretched zones and vertical cliffs can be related to fracture toughness and yield stress. Consequently, these features were also examined to determine whether any evidence could be found of a relationship between fracture toughness and stretched zones and cliff heights in the fracture toughness specimens of the three materials having relatively large differences in grain structure.

The stretched zone lay between the fatigue striations of the fatigue precrack and the dimpled region of typical tensile overload. It represented the first plastic deformation at the tip of the fatigue crack. When fracture occurred, it tended to leave a cliff representing a displacement between the tensile fracture plane and the fatigue fracture plane.

In the unrecrystallized sample the cliffs were not continuous and some small dimples were present on the cliff surface (Fig. F18a). In the recrystallized sample (Fig. F18b) also the cliffs were not continuous, and, in most regions, were almost featureless and free

of dimples. This probably reflected the tendency for cracks to follow grain boundaries in this material. Similar discontinuous cliffs were observed in the unrecrystallized plus hot rolled sample (Fig. F18c). Except for the recrystallized sample (Fig. F18b), the stretched zones could not be clearly identified.

Microstructure of Rapidly-Quenched Samples

As will be discussed later, the mode of fracture seemed to be partly related to the grain boundary particles (constituent particles and precipitate particles). To eliminate some of the precipitate particles, a faster quenching rate was obtained by using smaller specimens (0.6" ϕ). As shown in Fig. F19, the amount of grain boundary precipitate was to some extent reduced by the more rapid quench. Notch toughness data indicated that toughnesses of all three materials was increased by the rapid quench, but the ranking was the same as for the bulk-quenched samples. The same kinds of fracture modes were observed regardless of quenching rate.

DISCUSSION

One of the most important findings in this study was that fracture toughness increased as the proportion of intergranular fracture decreased. The unrecrystallized sample showed the highest fracture toughness and fractured almost entirely by the transgranular mode. On the other hand, the recrystallized sample showed lower fracture toughness which corresponded with a fracture that was almost entirely intergranular. The recrystallized plus hot rolled sample had a mixed transgranular-intergranular mode of fracture.

Several investigators^(8,9) have pointed out a relationship between fracture toughness and stretched zone width (and cliff heights). In this study, stereo pairs of fractographs revealed that the cliff height appeared to increase with increasing level of fracture toughness. Peel et al⁽⁹⁾ reported that higher fracture toughness was associated with the larger cliff height and that over considerable portions of the crack fronts, stretched zones were not observed. In the present investigation because of discontinuous cliff heights and irregular stretched zones, no clear relationship was obtained. Rather it was found that fracture toughness was closely related to the percentage of intergranular fracture. Therefore, observed differences in cliff height were not sufficient to give information on the fracture toughness, and the mode of fracture was the most important factor controlling the fracture toughness. A similar conclusion was made on Al-Zn-Mg-Cu-Zr alloys by DiRusso, et al⁽¹⁰⁾.

Intergranular fracture ensues when the matrix is stronger than the grain boundary and depends upon the grain boundary morphology and mutual orientation relationships with respect to the tension axis. The effect of precipitate-free zones (PFZ) on ductility or toughness has been studied by many investigators. Varley et al⁽¹¹⁾ postulated that preferential deformation within a PFZ might improve ductility due to a reduction in stress concentration at the grain boundary. Unwin and Smith⁽¹³⁾ found that the PFZ width had little effect on ductility and fracture toughness of Al-6%Zn-3%Mg alloy. However,

they pointed out that deformation might be concentrated in certain favorably oriented PFZ. As shown in Fig. F7a, the PFZ in the present materials was minimal even in the recrystallized sample which showed predominantly intergranular fracture. Such a narrow PFZ is not expected to control the intergranular fracture. Therefore, in this study, the fracture toughness and ductility were not believed to be appreciably affected by PFZ width. Similar results were obtained by Kirman⁽¹⁴⁾ who concluded that the fracture of 7075 was not primarily affected by PFZ width.

Preferential deformation along grain boundaries in the recrystallized and recrystallized plus hot rolled samples is shown in Figs. F7b and F8b. The sources of the dislocations observed along the grain boundaries are a special type termed grain boundary dislocations^(5,6), and they move along the boundary when the boundaries are mobile. Preferential deformation along grain boundaries might lead to an intergranular fracture and low toughness as was actually observed in these materials. In the case of the unrecrystallized sample, which showed a transgranular fracture mode and the highest toughness, no preferential deformation was observed along the grain boundary (Fig. F6a). The dislocation pile-ups shown in the recrystallized and recrystallized plus hot rolled materials (Figs. F7b and F8b) would also favor the intergranular fracture.

Another significant difference in the microstructures among the three treatments was the grain boundary particles (Fig. Fla-F1c). The recrystallized sample with low fracture toughness had preferential distribution of large particles (insoluble constituents

and η particles) along the grain boundary. This evidence suggests that the large $\text{Al}_7\text{Cu}_2\text{Fe}$ constituent particles, which formed prior to the recrystallization treatments, in addition to the smaller E-phase dispersoids acted as obstacles to the growth of new grains during recrystallization and for this reason could be found at the recrystallized grain boundaries. The small η particles probably formed along these boundaries during quenching and/or aging following the solution heat treatment.

The fractographic, microstructural and slip line study evidence suggests that the mechanism of intergranular fracture in the recrystallized material is the nucleation of voids by fracture of the large grain boundary precipitates and the $\text{Al}_7\text{Cu}_2\text{Fe}$ constituents followed by void coalescence associated with grain boundary dislocations and by matrix dislocation pile-ups affecting a force normal to the grain boundaries. Kirman⁽¹⁴⁾ also suggested that the intergranular fracture in 7075 occurs by the ductile void-coalescence mechanism.

The unrecrystallized sample which showed predominantly transgranular fracture did not have coarse particles located preferentially along the grain boundaries (Fig. Fla). Cracks were initiated mostly at slip bands (Fig. F9b). Also shown in the figure is the concentration of slip around large particles. When the size of the small dimples was compared to the average interparticle distance of the E phase, it was concluded that the small dimples were formed by the formation of voids at dispersoids (E phase) during straining with eventual void coalescence.

The Cr-bearing E phase particles were inhomogeneously distributed. This was especially apparent in the recrystallized samples. Actually there is no reason to anticipate that the distribution should be different among the different structures investigated, since the Cr does not diffuse from its initial dendritic segregation pattern but precipitates essentially in situ⁽¹⁵⁾. The distribution of Cr, Mg, Cu and Zn in 7475 was studied by Flemings and his co-workers⁽¹⁶⁾. They reported significant segregation of Cu and Cr in a cast ingot (high Cr at the dendritic center and high Cu in the interdendritic region) and Cr segregation was very difficult to reduce with thermomechanical treatments. Our electron microprobe examination on light microscope scale showed that after thermomechanical treatments the concentration of Cr did not significantly vary across the grains even though the distribution of dispersoids changed from grain to grain or even inside the grain as shown in the transmission electron micrographs (Figs. F3a, F3b, F4a, F4b, and F5). inhomogeneous distribution of E phase did not seem to affect the mechanical properties appreciably.

CONCLUSIONS

1. The fracture toughness of 7475 plate processed to have different grain structure was most significantly affected by the fracture mode. The unrecrystallized plate showed a predominantly transgranular fracture mode and had a higher fracture toughness than the recrystallized plate which showed an almost entirely

intergranular mode. The toughness of the recrystallized plus hot rolled plate was intermediate, and fracture mode was mixed transgranular-intergranular.

2. The intergranular fractures were attributed to nucleation of voids at grain boundaries by large constituent and precipitate particles and by coalescence of these voids through an interaction of dislocations with the grain boundaries.


3. Fractographic features such as stretched zones and cliff heights were not prominent as indicators of relative fracture toughness of 7475.

REFERENCES

1. M.S.Hunter and J.C.McMillan, ASTM STP 436, ASTM, Philadelphia (1968), p. 196.
2. S. Samson, Acta Cryst., 11, 851 (1958).
3. G. Lütjering and E. Hornbogen, Z. Metallk. 59, 29 (1968).
4. G. Lütjering and S. Weissmann, Acta Met., 18, 785 (1970).
5. H. Gleiter, E. Hornbogen, and G. Bäro, Acta Met. 16, 1053 (1968).
6. G. Bäro, H. Gleiter, and E. Hornbogen, Mater. Sc. Eng. 3, 92 (1968/69).
7. C. W. Price and J. P. Hirth, Mater. Sci. Eng. 9, 15 (1972).
8. R. C. Bates and W. G. Clark, Trans. ASM 62, 380 (1969).
9. C. J. Peel, R. N. Wilson and P. J. E. Forsyth, J. Metal Sci. 6, 102 (1972).
10. E. DiRusso, G. Oddone, F. Gatto and M. Buratti, Alluminio, N 7/8, 415 (1974).
11. P. C. Varley, M. K. B. Day and A. Sendorek, J. Inst. Metals, Vol. 86, 337 (1957-58).
12. N. Ryum, Acta Met. 16, 327 (1968).
13. P. N. T. Unwin and A. C. Smith, J. Inst. Metals 97, 299 (1969).
14. I. Kirman, Met. Trans. 2, 1761 (1971).
15. H. Y. Hunsicker, Aluminum, K. R. Van Horn, ed., ASM (1967), Vol. 1, p. 129.
16. J. J. Michalek, E. S. Palmer, R. G. Riek, R. Mehrabian, and M. C. Flemings, Report - Contract No. DAAG25-73-C-0196, Frankford Arsenal, Philadelphia (1973).




500X




2000X

Fig. Fla - Micrographs (SEM) showing the distribution of particles in the unrecrystallized sample.



500X




2000X

Fig. Flb - Micrographs (SEM) showing the distribution of particles in the recrystallized sample.




500X



2000X

Fig. Flc - Micrographs (SEM) showing the distribution of particles in the recrystallized plus hot rolled sample.



MAG: 100X

ETCH: KELLERS

1.50" THICK 7475-T6 PLATE S-418967-50


INGOT				SLAB				RECRYSTALLIZATION				PLATE					
THERMAL ⁽¹⁾		ROLLING		THICK	THERMAL ⁽¹⁾		ROLLING		THICK	ROLLING		SOLUTION ⁽¹⁾	GRAIN COUNT				
TREATMENT	TEMP	RGD	TREATMENT		TEMP	RGD	TREATMENT	AT 750°F		RGD	HEAT-TREAT		g/mm			g/mm ³	
													X	Y	Z	XYZ	
6hr/860°F		750°F	14%	8 0"	2hr/960°F		500°F	75%	2 0"	8hr/960°F	25%	2 hr/960°F	24	11	62	16 368	
20hr/960°F					2hr/775°F												
					4hr/500°F												

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _Q ksi√in.
L	82.1	70.6	17.1	28	97.1	1.37	29.9
T	80.5	69.0	15.0	25	84.7	1.23	29.2
N	79.3	66.3	12.0	N.D.	79.2	1.20	29.0

MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK RECRYSTALLIZED
AND HOT ROLLED (AR+HR) 7475-T6 PLATE S-418967-50

Figure F2a



MAG:100X

ETCH:KELLERS

1.50" THICK 7475-T6 PLATE S-418967-40


INGOT			SLAB			RECRYSTALLIZATION			PLATE						
		ROLLING				ROLLING						GRAIN COUNT			
THERMAL TREATMENT	TEMP	RGD	THICK	THERMAL TREATMENT	TEMP	RGD	THICK	THERMAL TREATMENT	At 750 F RGD	SOLUTION HEAT TREAT	g/mm			g/mm	
											X	Y	Z	XYZ	
6hr 860 F	750 F	35%	6.0"	2hr/960 F	500 F	75%	1.50"	18hr/960 F	NONE	2hr 960 F	22	20	54	23 760	
20hr 960 F				2hr/775 F											
				4hr/500 F											

(1) THERMAL TREATMENTS CARRIED OUT IN A CIRCULATING AIR FURNACE

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K ₀ ksi√in.
L	79.3	67.7	17.9	32	90.1	133	32.4
T	80.2	68.5	15.7	22	82.1	120	27.5
N	79.3	67.4	8.0	N.D.	85.0	127	23.6

MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK RECRYSTALLIZED (AR) 7475-T6 PLATE S-418967-40

Figure F2b



MAG: 100X


ETCH: KELLERS

1.50" THICK HOT ROLLED (HR) 7475-T6 PLATE S-418967-30

PROPERTIES							
DIR	T.S. ksi	Y.S. ksi	EL %	R.A. %	N.T.S. ksi	N.T.S. Y.S.	K _Q ksi√in.
L	83.8	73.0	15.0	19	99.8	1.37	40.9
T	81.3	70.3	15.7	21	90.0	1.28	32.6
N	81.4	67.1	10.0	N.D.	85.3	1.28	31.0


MICROSTRUCTURE AND PROPERTIES OF 1.50" THICK HOT ROLLED
(HR) 7475-T6 PLATE S-418967-30

Figure F2c




8600X

Fig. F3a - Micrograph (TEM) of undeformed unrecrystallized material. Note the cells and dislocations inside the subgrains. The small particles ($\sim 0.05\mu\text{m}$ to $\sim 0.15\mu\text{m}$) are mostly the E phase.




15,000X

Fig. F3b - Micrograph (TEM) of undeformed unrecrystallized material. Note the small M' or M particles along the subgrain.




11,800X

Fig. F4a - Micrograph (TEM) of undeformed recrystallized material. Note the large constituent particles along grain boundary.




11,800X

Fig. F4b - Micrograph (TEM) of undeformed recrystallized material. Note the inhomogeneous distribution of the E phase.




15,000X

Fig. F5 - Micrograph (TEM) of undeformed recrystallized plus hot rolled material. Note the polygonized structure due to hot rolling following recrystallization.



72,000X

Fig. F6a - Micrograph (TEM) representing the uniformly deformed regions of unrecrystallized material. Note the relatively homogeneous distribution of dislocations.




36,000X

Fig. F6b - Micrograph (TEM) representing the uniformly deformed regions of unrecrystallized material. Note the fractured rod-shaped particles.




44,000X

Fig. F7a - Micrograph (TEM) showing the uniformly deformed regions of the recrystallized material. Note the η' particles with a few E particles inside the grain and the interaction between dislocation bands and the grain boundary.




26,000X

Fig. F7b - Micrograph (TEM) showing the uniformly deformed regions of the recrystallized material. Note the preferential deformation of the grain boundary.




19,600X

Fig. F8a - Micrograph (TEM) showing the uniformly deformed regions of the recrystallized plus hot rolled material. Note the interaction between grain boundaries and dislocation bands.



44,000X

Fig. F8b - Micrograph (TEM) showing the uniformly deformed regions of the recrystallized plus hot rolled material. Note the preferential deformation at the grain boundary.



250X

Fig. F9a - Optical micrograph showing the slip line structure in the uniformly deformed region (L-T plane) of the unrecrystallized material. Note the well developed slip bands and the concentration of slip around large constituent particles.




250X

Fig. F9b - Optical micrograph showing the slip line structure in the necked region (L-T plane) of the unrecrystallized material. Note that fracture predominantly followed slip bands.




250X

Fig. F9c - Optical micrograph showing the fracture in the L-N plane of the unrecrystallized material. Note that fracture was initiated at the coarse constituents in many regions.




250X

Fig. F10a - Optical micrograph showing the slip line structure (L-T plane) in the uniformly deformed region of the recrystallized material. Note the grain boundary sliding in this material.



250X

Fig. F10b - Optical micrograph showing the slip line structure (L-T plane) in the necked region of the recrystallized material. Note that cracking occurred mostly along grain boundaries.




250X

Fig. F10c - Optical micrograph showing fracture in the L-N plane of the recrystallized material. Note that fracture path is predominantly intergranular.




250X

Fig. F11a - Optical micrograph showing the slip line structures (L-T plane) in the uniformly deformed region of the recrystallized plus hot rolled material. Note the initiation of cracks at the grain boundaries and also at the slip bands.




250X

Fig. F11b - Optical micrograph showing the slip line structures (L-T plane) in the necked region of the recrystallized plus hot rolled material. Note the intergranular-transgranular (mixed) mode of fracture.



250X

Fig. F11c - Optical micrograph showing the fracture in the L-N plane of recrystallized plus hot rolled material.



a.


200X



b.


1000X

Fig. F12 - Fractographs of fracture toughness specimen (L-T) of unrecrystallized material showing predominantly transgranular fracture.



a.


200X



b.


1000X

Fig. F13 - Fractographs of fracture toughness specimen (L-T) of recrystallized material showing predominantly intergranular fracture.



a.

200X



b.


1000X

Fig. F14 - Fractographs of fracture toughness specimen (L-T) of recrystallized plus hot rolled material showing a mixed mode intergranular-transgranular fracture.



a.


100X



b.


500X

Fig. F15 - Fractographs of L notched tensile specimen of unrecrystallized material. Note the predominantly transgranular mode of fracture.



a.


100X



b.


500X

Fig. F16 - Fractographs of L notched tensile specimen of recrystallized material. Note the predominantly intergranular mode of fracture.



a.

100X




b.

500X


Fig. F17 - Fractographs of L notched tensile specimen of recrystallized plus hot rolled material. Note the mixed mode intergranular-transgranular fracture.



a. Unrecrystallized 1000X




b. Recrystallized 1000X




c. Recrystallized plus
hot rolled 1000X

Fig. F18 - Scanning electron fractographs of fracture toughness specimens at the fatigue/overload transition regions. Shown are the fatigue precrack (f), the stretched zone (s), the cliff (c) and overload fracture (o).



a. Recrystallized 2000X



b. Recrystallized plus
hot rolled 500X

Fig. 19 - Scanning electron micrographs of rapidly quenched samples.

DISTRIBUTION LIST

Office, Chief of Research and
Development
Department of the Army
Attn: DARD-ARS-PM
Washington, DC 20310

Department of Defense
Attn: Advanced Research and
Technology Div.
Washington, DC 20310

Commander
US Army Materiel Development and
Readiness Command
5001 Eisenhower Ave
Alexandria, VA 22333
Attn: DRCMT, Col. N. Vinson
Attn: DRCDMD
Attn: DRCDMR
Attn: DRCDMD-T
Attn: DRCDE-I
Foreign Science and
Technology Div.
Attn: DRCDE-W
Attn: DRCMT, L. Croan
Attn: DRCDE-E, E. Gardner
Attn: DRCDE-DE, E. Lippi

Commander
US Army Armament Command
Rock Island, IL 61201
Attn: DRSAR-RD, J. Brinkman
Attn: DRSAR-RDG-A, J. Williams
Attn: PM, CAWS, H. Noble
Attn: DRSAR-PPR-1W
Attn: DRSAR-PPI-W, A. Zahatko
Attn: Technical Information Div.

Commander
US Army Tank Automotive Research and
Development Command
Warren, MI 48090
Attn: DRDTA-RCM.1
Attn: DRDTA-RKA, V. Pagano
Attn: DRDTA-RKA, H. Spiro (3)

Project Manager
XM-1 Tank System
28150 Dequindre
Attn: AMCPM-GCM-SMA, J. Roossien
Warren, MI 48092

Commander
US Army Aviation Systems Command
P.O. Box 209
St. Louis, MO 63166
Attn: DRSV-EXT
Attn: Technical Information Div.

Commander
US Army Electronics Command
Ft. Monmouth, NJ 07703
Attn: AMSEL-RD-P
Attn: Technical Information Div.

Commander
US Army Missile Command
Redstone Arsenal, AL 35809
Attn: DRSMI-IIE
Attn: DRSMI-RSM
Attn: Technical Information Div.

Commander
US Army Troop Support Command
Attn: AMSTS-PLC
4300 Goodfellow Blvd
St. Louis, MO 63120

Commander
US Army Materials and Mechanics
Research Center
Watertown, MA 02172
Attn: DMXMR, Dr. E. Wright
Attn: DMXMR-PT
Attn: Technical Information Div.

Commander
US Army Mobility Equipment
Research and Development Command
Attn: STSFB-MMM
Ft. Belvoir, VA 22060

Commander
Rock Island Arsenal
Attn: Technical Information Div.
Rock Island, IL 61202

Commander
Picatinny Arsenal
Dover, NJ 07801
Attn: PM, Selected Ammunition
Attn: SARPA-AD
Attn: SARPA-FR-M
Attn: Technical Information Div.

Project Manager for Munition Production
Base Modernization and Expansion
Dover, NJ 07801
Attn: DRCPM-PBM-M, H. Krosser
Attn: DRCPM-PBM-M

Commander
Watervliet Arsenal
Watervliet, NY 12189
Attn: SARV-RDR, Dr. T. E. Davidson
Attn: Technical Information Div.

Commander
US Army Research Office
P.O. Box 12211
Attn: Dr. George Mayer, Director
Metallurgy & Materials Science Div.
Research Triangle Park, NC 27709

Commander
US Army Research & Standardization
Group (Europe)
Attn: DRXSN-E-RM, Dr. R. Quattrone
Box 65
FPA New York 09510

Commander
Aberdeen Proving Ground
Aberdeen, MD 21005
Attn: AMXBR-TB-E, Dr. E. E. Bloore
Attn: STEAP-TL, Technical Library

Commander
Harry Diamond Laboratories
2800 Powder Mill Road
Attn: AMXDO-TB
Adelphi, MD 20783

Commander
Redstone Arsenal
Attn: Technical Information Div.
Huntsville, AL 35809

Commander
Rocky Mountain Arsenal
Attn: Technical Information Div.
Denver, CO 80240

Commander
US Army Natick Research and
Development Command
Attn: Technical Information Div.
Natick, MA 07160

Commander
Edgewood Arsenal
Attn: Technical Information Div.
Edgewood, MD 21005

Director
US Army Industrial Base Engineering
Activity
Rock Island, IL 61201
Attn: DRXIB-MT, G. Ney
Attn: DRXPE, J. Gallagher

Commander
US Army Foreign Science and
Technology Center
Attn: Mr. William F. Marley
220 7th Street N.E.
Charlottesville, VA 22901

Director
Air Force Armament Laboratory
Attn: AFATL/DLOSL
Eglin AFB, FL 32542

Commander
Air Research and Development
Command
Andrews Air Force Base
Attn: RDRAA
Washington, DC 20025

Director
Air Force Materials Laboratory
Wright Patterson AFB
Dayton, OH 45433
Attn: AFML/XR, Dr. T. M. F. Ronald
Attn: AFML, Technical Library
Attn: AFML/LTM, N. Klarquist
Attn: AFML/LTN
Attn: AFML/LTE
Attn: AFML/LLN, Dr. V. Russo
Attn: AFML/LLS, W. Griffith

Director
Air Force Weapons Laboratory
Attn: Technical Information Div.
Kirtland AFB, NM 87118

Commander
Naval Air Systems Command
Department of the Navy
Attn: AIR 5203, Mr. R. Schmidt
Washington, DC 20361

Commander
Naval Ships Systems Command
Department of the Navy
Attn: Code 03423
Washington, DC 20025

Commander
Office of Naval Research
Department of the Navy
Attn: Code 423
Washington, DC 20025

Commander
US Naval Weapons Laboratory
Attn: Technical Information Div.
Dahlgren, VA 22448

Commander
Naval Air Development Center
Johnsville
Aero Materials Dept
Attn: F. Williams
Warminster, PA 18974

Chief, Bureau of Ships
Department of the Navy
Attn: Code 343
Washington, DC 20025

Chief, Bureau of Aeronautics
Department of the Navy
Attn: Technical Information Div.
Washington, DC 20025

Chief, Bureau of Weapons
Department of the Navy
Attn: Technical Information Div.
Washington, DC 20025

Commander
US Naval Engineering Experimental
Station
Attn: WCTRL-2 Materials Lab
Annapolis, MD 21402

Commander
US Naval Ordnance Laboratory
Attn: CODE WM
Silver Spring, MD 20910

Director
US Army Advanced Materials Concept
Agency
Attn: Technical Information Div.
2461 Eisenhower Avenue
Alexandria, VA 22314

Director
US Naval Research Laboratory
Attn: W. S. Pellini
Code 6300, Metallurgy Div.
Washington, DC 20390

Director
Naval Ships Research and
Development Center
Attn: A. R. Willmer
Chief of Metals Research
Bethesda, MD 20034

Commander
US Naval Ordnance Station
Attn: Code FS-72C, T. Mycka
Indianhead, MD 20640

Director
Defense Advanced Research Projects
Agency
Attn: Dr. E. C. Van Reuth
1400 Wilson Boulevard
Arlington, VA 22209

Director
National Academy of Science
Attn: Materials Advisory Board
2101 Constitution Ave., N.W.
Washington, DC 20418

Director
National Aeronautics and Space
Administration
Attn: Code RRM
Federal Building #10
Washington, DC 20546

Director
National Aeronautics and Space
Administration
George C. Marshall Space Flight
Center
Attn: M-F&AR-M, W. Wilson
Huntsville, AL 35800

Director
National Bureau of Standards
Attn: Technical Information Div.
Washington, DC 20025

Director
US Atomic Energy Commission
Attn: Document Library
Germantown, MD 21403

Federal Aviation Administration
Attn: Administrative Standard Div.
800 Independence Avenue, S.W.
Washington, DC 20590

Metals and Ceramic Information
Center
Battelle Memorial Institute
505 King Avenue
Columbus, OH 43201

Defense Documentation Center (12)
Cameraon Station
Attn: DDC-TCA
Alexandria, VA 22314

Mr. Robert H. Brown
1411 Pacific Avenue
Natrona Heights, PA 15065

Dr. Robert S. Rusk
3606 Windsor Court
Midland, MI 48640

Mr. J. B. Hess
Kaiser Aluminum & Chemical Corp.
Aluminum Division Research Center
for Technology
P.O. Box 870
Pleasanton, CA 94566

Prof. G. R. Irwin
University of Maryland
College Park, MD 20740

Dr. Schrade Radtke
International Lead Zinc Institute
292 Madison Avenue
New York, NY 10017

Prof. M. C. Flemings
Department of Metallurgy and
Materials Science
Mass. Institute of Technology
Cambridge, MA 02139

Mr. Carson L. Brooks
Reynolds Metal Company
4th & Canal Streets
Richmond, VA 23219

Mr. Harold Hunsicker
Aluminum Company of America
Alcoa Technical Center
Alcoa Center, PA 15069

Prof. J. Kenig
Drexel University
Philadelphia, PA 19104

Dr. E. J. Ripling
Materials Research Laboratory, Inc.
1 Science Road
Glenwood, IL 60425

Prof. H. Rogers
Drexel University
Philadelphia, PA 19104

Dr. LaVerne W. Eastwood
Rt. #2
Woodfield, OH 43793

Dr. William Rostoker
University of Illinois
College of Engineering
Box 4348
Chicago, IL 60680

Mr. Joseph C. Zola
Boeing Vertol Company
P.O. Box 16858
M/S P32-38
Philadelphia, PA 19142

Prof. Campbell Laird
Dept. of Metallurgy & Materials
Science
University of Pennsylvania
Philadelphia, PA 19174

Mr. M. V. Hyatt
Organization B-8833
Mail Stop 73-43
The Boeing Company
P.O. Box 3707
Seattle, WA 98124

Prof. Robert Mehrabian
University of Illinois at
Urbana-Champaign
Urbana, IL 61801

Dr. N. Paton
Rockwell International Science
Center
Thousand Oaks, CA 91360

Commander (15)
Frankford Arsenal
Attn: PDM-P, L3100, Bldg. 513,
Dr. J. Waldman
Bridge and Tacony Streets
Philadelphia, PA 19137

DISCLAIMER NOTICE

**THIS DOCUMENT IS BEST QUALITY
PRACTICABLE. THE COPY FURNISHED
TO DTIC CONTAINED A SIGNIFICANT
NUMBER OF PAGES WHICH DO NOT
REPRODUCE LEGIBLY.**